

SABIC Innovative Plastics Lexan® AD143 PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

LEXAN AD143 is a medium viscosity, injection molding grade exhibiting low dust attraction. It is designed for applications with high optical requirements in terms of clarity and light transmission and is also available in opaque colors.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-AD143-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Moisture Absorption	0.150 %	0.150 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.35 %	0.35 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	13 g/10 min @Load 1.20 kg, Temperature 300 °C	13 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238
Melt Index of Compound	12 g/10 min @Load 1.20 kg, Temperature 300 °C	12 g/10 min @Load 2.65 lb, Temperature 572 °F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, H358/30	95.0 MPa	13800 psi	ISO 2039-1
Tensile Strength at Break	69.0 MPa	10000 psi	Type I, 50 mm/min; ASTM D638
	70.0 MPa	10200 psi	50 mm/min; ISO 527
Tensile Strength, Yield	62.0 MPa	8990 psi	Type I, 50 mm/min; ASTM D638
	63.0 MPa	9140 psi	50 mm/min; ISO 527
Elongation at Break	120 %	120 %	50 mm/min; ISO 527
	130 %	130 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	6.0 %	6.0 %	50 mm/min; ISO 527

Mechanical Properties	Metric	English	Comments
			Type I, 50 mm/min; ASTM D638
Tensile Modulus	2.30 GPa	334 ksi	5 mm/min; ASTM D638
	2.35 GPa	341 ksi	1 mm/min; ISO 527
Flexural Yield Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
	97.0 MPa	14100 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.30 GPa	334 ksi	2 mm/min; ISO 178
	2.34 GPa	339 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	8.01 J/cm	15.0 ft-lb/in	ASTM D256
	1.25 J/cm	2.34 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Notched (ISO)	70.0 kJ/m ²	33.3 ft-lb/in ²	80*10*3; ISO 180/1A
	12.0 kJ/m ²	5.71 ft-lb/in ²	80*10*3; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	NB	NB	80*10*3; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	7.30 J/cm ²	34.7 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	1.40 J/cm ²	6.66 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Dart Drop, Total Energy	64.0 J	47.2 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Taber Abrasion, mg/1000 Cycles	10	10	CS-17, 1 kg; SABIC Method

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 µm/m-°C	38.9 µin/in-°F	ASTM E 831

Thermal Properties	Metric	English	Comments
	70.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	38.9 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	ISO 11359-2
	@Temperature 23.0 - 80.0 $^\circ\text{C}$	@Temperature 73.4 - 176 $^\circ\text{F}$	
CTE, linear, Transverse to Flow	70.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	38.9 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	ASTM E 831
	@Temperature -40.0 - 40.0 $^\circ\text{C}$	@Temperature -40.0 - 104 $^\circ\text{F}$	
	70.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	38.9 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	ISO 11359-2
	@Temperature 23.0 - 80.0 $^\circ\text{C}$	@Temperature 73.4 - 176 $^\circ\text{F}$	
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft ² - $^\circ\text{F}$	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	135 $^\circ\text{C}$	275 $^\circ\text{F}$	Edgew 120*10*4 sp=100mm; ISO 75/Be
Deflection Temperature at 1.8 MPa (264 psi)	123 $^\circ\text{C}$	253 $^\circ\text{F}$	Edgew 120*10*4 sp=100mm; ISO 75/Ae
	114 $^\circ\text{C}$	237 $^\circ\text{F}$	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
	130 $^\circ\text{C}$	266 $^\circ\text{F}$	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Vicat Softening Point	140 $^\circ\text{C}$	284 $^\circ\text{F}$	Rate B/50; ISO 306
	141 $^\circ\text{C}$	286 $^\circ\text{F}$	Rate B/120; ISO 306
	153 $^\circ\text{C}$	307 $^\circ\text{F}$	Rate B/50; ASTM D1525
Glow Wire Test	850 $^\circ\text{C}$	1560 $^\circ\text{F}$	IEC 60695-2-12
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Optical Properties	Metric	English	Comments
Refractive Index	1.586	1.586	ISO 489
Haze	$\leq 0.80\%$	$\leq 0.80\%$	ASTM D1003
	@Thickness 2.54 mm	@Thickness 0.100 in	
Transmission, Visible	89 %	89 %	2.54 mm; ASTM D1003

Electrical Properties	Metric	English	Comments
Surface Resistance	5.00e+13 ohm	5.00e+13 ohm	ASTM D257

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	Pass	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China