

SABIC Innovative Plastics Lexan® FXD941A PC

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

FXD153 is an Extrusion / Blow molding grade in a Diffusion effect, which is part of the VisualFX family. These effects have been developed to meet increasing Aesthetic demands in the Marketplace. Color Package may affect properties, Application testing always recommended.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-FXD941A-PC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	2.5 g/10 min @Load 1.20 kg, Temperature 300 °C	2.5 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	66.0 MPa	9570 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	62.0 MPa	8990 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	110 %	110 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	7.0 %	7.0 %	Type I, 50 mm/min; ASTM D638
Tensile Modulus	2.34 GPa	339 ksi	5 mm/min; ASTM D638
Flexural Yield Strength	93.0 MPa	13500 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.34 GPa	339 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	7.48 J/cm	14.0 ft-lb/in	ASTM D256
Izod Impact, Unnotched	32.04 J/cm	60.02 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear, Transverse to Flow	68.0 µm/m-°C @Temperature -40.0 - 40.0 °C	37.8 µin/in-°F @Temperature -40.0 - 104 °F	ASTM E 831
Deflection Temperature at 0.46 MPa (66 psi)	138 °C @Thickness 3.20 mm	280 °F @Thickness 0.126 in	unannealed; ASTM D648

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	152 °C @Thickness 3.20 mm	300 °F @Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	157 °C	315 °F	Rate B/50; ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China