

SABIC Innovative Plastics Lexan® FXE1112T PC Copolymer

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Lexan® FXE1112T Lexan® polycarbonate (PC) siloxane copolymer resin is a transparent injection molding grade. This resin offers good low temperature (-20 °C) ductility in combination with high flow characteristics and excellent processability with opportunities for shorter IM cycle times compared to standard PC. Lexan FXE1112T resin may be an excellent candidate for a broad range of applications. This product is available in GE Plastics' Visual fX® Piano Black, Raven Black & Illuminate color range only.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-FXE1112T-PC-Copolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.19 g/cc	1.19 g/cc	ASTM D792
Density	1.19 g/cc	0.0430 lb/in ³	ISO 1183
Moisture Absorption	0.0900 %	0.0900 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.24 %	0.24 %	ISO 62
Linear Mold Shrinkage, Flow	0.0040 - 0.0080 cm/cm @Thickness 3.20 mm	0.0040 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	20 g/10 min @Load 1.20 kg, Temperature 300 °C	20 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238
Melt Index of Compound	19 g/10 min @Load 1.20 kg, Temperature 300 °C	19 g/10 min @Load 2.65 lb, Temperature 572 °F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	56.0 MPa	8120 psi	50 mm/min; ISO 527
	57.0 MPa	8270 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	57.0 MPa	8270 psi	50 mm/min; ISO 527
	58.0 MPa	8410 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	117.9 %	117.9 %	Type I, 50 mm/min; ASTM D638
	119.4 %	119.4 %	50 mm/min; ISO 527
Elongation at Yield	5.4 %	5.4 %	50 mm/min; ISO 527
	5.7 %	5.7 %	Type I, 50 mm/min; ASTM D638

Mechanical Properties	Metric	English	Comments
	2.34 GPa	339 ksi	1 mm/min; ISO 527
Flexural Yield Strength	89.0 MPa	12900 psi	2 mm/min; ISO 178
	94.0 MPa	13600 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.14 GPa	310 ksi	2 mm/min; ISO 178
	2.24 GPa	325 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	7.36 J/cm	13.8 ft-lb/in	ASTM D256
	6.18 J/cm	11.6 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Notched (ISO)	65.0 kJ/m²	30.9 ft-lb/in²	80*10*3; ISO 180/1A
	55.0 kJ/m²	26.2 ft-lb/in²	80*10*3; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	NB	NB	80*10*3; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	6.50 J/cm²	30.9 ft-lb/in²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	4.50 J/cm²	21.4 ft-lb/in²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Dart Drop, Total Energy	74.0 J	54.6 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	74.8 µm/m-°C	41.6 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 95.0 °C	@Temperature -40.0 - 203 °F	
	74.8 µm/m-°C	41.6 µin/in-°F	

Thermal Properties	Metric	English	Comments
CTE, linear, Transverse to Flow	76.4 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	42.4 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	ASTM E 831
	@Temperature 23.0 - 80.0 $^{\circ}\text{C}$	@Temperature 73.4 - 176 $^{\circ}\text{F}$	
	76.4 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	42.4 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	ISO 11359-2
	@Temperature -40.0 - 95.0 $^{\circ}\text{C}$	@Temperature -40.0 - 203 $^{\circ}\text{F}$	
Deflection Temperature at 1.8 MPa (264 psi)	116 $^{\circ}\text{C}$	241 $^{\circ}\text{F}$	Flatw 80*10*4 sp=64mm; ISO 75/Af
	121 $^{\circ}\text{C}$	250 $^{\circ}\text{F}$	
Vicat Softening Point	138 $^{\circ}\text{C}$	280 $^{\circ}\text{F}$	Rate A/50; ASTM D1525
	138 $^{\circ}\text{C}$	280 $^{\circ}\text{F}$	
	139 $^{\circ}\text{C}$	282 $^{\circ}\text{F}$	Rate B/120; ISO 306

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China