

SABIC Innovative Plastics Lexan® FXE1414L PC Copolymer (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Opaque EXL, UV-Stabilized & light shielding capability (Wall thickness >0.8mm), for portable electronics device enclosure application. Only available in white, grey and limited pastel colors. Consult CIC or PM for color availability & limitation. This data was supplied by SABIC-IP for the Europe-Africa-Middle East region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-FXE1414L-PC-Copolymer-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.28 g/cc	1.28 g/cc	ASTM D 792
Density	1.28 g/cc	0.0462 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.070 %	0.070 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.17 % @Temperature 23.0 °C	0.17 % @Temperature 73.4 °F	ISO 62
Linear Mold Shrinkage, Flow	0.0040 - 0.0080 cm/cm @Thickness 3.20 mm	0.0040 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	10 g/10 min @Load 1.20 kg, Temperature 300 °C	10 g/10 min @Load 2.65 lb, Temperature 572 °F	[cm ³ /10 min] Melt Volume Rate; ISO 1133
	11 g/10 min @Load 1.20 kg, Temperature 300 °C	11 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	47.0 MPa	6820 psi	50 mm/min; ISO 527
	54.0 MPa	7830 psi	Type I, 50 mm/min; ASTM D 638
Tensile Strength, Yield	52.0 MPa	7540 psi	Type I, 50 mm/min; ASTM D 638
	52.0 MPa	7540 psi	50 mm/min; ISO 527
Elongation at Break	75 %	75 %	50 mm/min; ISO 527
	84 %	84 %	Type I, 50 mm/min; ASTM D 638
Elongation at Yield	5.0 %	5.0 %	Type I, 50 mm/min; ASTM D 638

Mechanical Properties	5.0 % Metric	5.0 % English	50 mm/min; ISO 527 Comments
Tensile Modulus	2.00 GPa	290 ksi	1 mm/min; ISO 527
	2.03 GPa	294 ksi	50 mm/min; ASTM D 638
Flexural Yield Strength	83.0 MPa	12000 psi	2 mm/min; ISO 178
	86.0 MPa	12500 psi	1.3 mm/min, 50 mm span; ASTM D 790
Flexural Modulus	2.05 GPa	297 ksi	1.3 mm/min, 50 mm span; ASTM D 790
	2.11 GPa	306 ksi	2 mm/min; ISO 178
Izod Impact, Notched	6.40 J/cm	12.0 ft-lb/in	ASTM D 256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	7.66 J/cm	14.4 ft-lb/in	ASTM D 256
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Impact Test	68.0 J	50.2 ft-lb	Instrumented Impact Total Energy; ASTM D 3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 µm/m-°C	38.9 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	70.2 µm/m-°C	39.0 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
CTE, linear, Transverse to Flow	67.3 µm/m-°C	37.4 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	82.3 µm/m-°C	45.7 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Deflection Temperature at 1.8 MPa (264 psi)	118 °C	244 °F	Flatw 80*10*4 sp=64mm; ISO 75/ Af
	121 °C	250 °F	unannealed; ASTM D 648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	138 °C	280 °F	Rate B/50; ASTM D 1525
	138 °C	280 °F	Rate B/50; ISO 306

Thermal Properties	Metric	English	Comments
	140 °C	200 °F	HAZ 0, 120; ISO 306
Flammability, UL94	HB	HB	UL 94
	@Thickness 0.400 mm	@Thickness 0.0157 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China