

SABIC Innovative Plastics Lexan® FXM1413T PC Copolymer (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

PC-siloxane copolymer in special metallic colors. Medium flow. Improved toughness compared to medium flow standard PC in same color.

Color package may affect performance. This data was supplied by SABIC-IP for the Europe-Africa-Middle East region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-FXM1413T-PC-Copolymer-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.18 g/cc	1.18 g/cc	ASTM D 792
Density	1.18 g/cc	0.0426 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.090 %	0.090 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.12 % @Temperature 23.0 °C	0.12 % @Temperature 73.4 °F	ISO 62
Linear Mold Shrinkage, Flow	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	on tensile bar; SABIC Method
	0.0040 - 0.0080 cm/cm @Thickness 3.20 mm	0.0040 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0040 - 0.0080 cm/cm @Thickness 3.20 mm	0.0040 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	9.0 g/10 min @Load 1.20 kg, Temperature 300 °C	9.0 g/10 min @Load 2.65 lb, Temperature 572 °F	[cm ³ /10 min] Melt Volume Rate; ISO 1133
	10 g/10 min @Load 1.20 kg, Temperature 300 °C	10 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	54.0 MPa	7830 psi	50 mm/min; ISO 527
	56.0 MPa	8120 psi	Type I, 50 mm/min; ASTM D 638
Tensile Strength, Yield	57.0 MPa	8270 psi	50 mm/min; ISO 527
	58.0 MPa	8410 psi	Type I, 50 mm/min; ASTM D 638
Elongation at Break	105 %	105 %	50 mm/min; ISO 527

Mechanical Properties	Metric	English	Comments
Elongation at Yield	5.6 %	5.6 %	50 mm/min; ISO 527
	5.9 %	5.9 %	Type I, 50 mm/min; ASTM D 638
Tensile Modulus	2.26 GPa	328 ksi	50 mm/min; ASTM D 638
	2.32 GPa	336 ksi	1 mm/min; ISO 527
Flexural Yield Strength	86.0 MPa	12500 psi	1.3 mm/min, 50 mm span; ASTM D 790
	89.0 MPa	12900 psi	2 mm/min; ISO 178
Flexural Modulus	2.17 GPa	315 ksi	2 mm/min; ISO 178
	2.27 GPa	329 ksi	1.3 mm/min, 50 mm span; ASTM D 790
Izod Impact, Notched	2.46 J/cm	4.61 ft-lb/in	ASTM D 256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	6.10 J/cm	11.4 ft-lb/in	ASTM D 256
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Impact Test	61.0 J	45.0 ft-lb	Instrumented Impact Total Energy; ASTM D 3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	71.5 µm/m-°C	39.7 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 95.0 °C	@Temperature -40.0 - 203 °F	
	71.5 µm/m-°C	39.7 µin/in-°F	ISO 11359-2
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	
CTE, linear, Transverse to Flow	79.3 µm/m-°C	44.1 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 95.0 °C	@Temperature -40.0 - 203 °F	
	79.3 µm/m-°C	44.1 µin/in-°F	ISO 11359-2
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	
Deflection Temperature at 1.8 MPa (264 psi)	120 °C	248 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	122 °C	252 °F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D 648

Thermal Properties Vicat Softening Point	Metric 141 °C	English 286 °F	Comments Rate B/50; ASTM D 1525
	141 °C	286 °F	Rate B/50; ISO 306
	143 °C	289 °F	Rate B/120; ISO 306

Descriptive Properties	Value	Comments
Ball Pressure Test, 75°C +/- 2°C	PASS	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China