

SABIC Innovative Plastics Lexan® FXM921A PC (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

LEXAN FXM921A is a transparent/translucent, medium viscosity, flame retardant grade with a metallic-luster appearance. Color package may affect performance. This data was supplied by SABIC-IP for the Europe-Africa-Middle East region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-FXM921A-PC-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.15 %	0.15 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.35 % @Temperature 23.0 °C	0.35 % @Temperature 73.4 °F	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	on tensile bar; SABIC Method
Melt Flow	12 g/10 min @Load 1.20 kg, Temperature 300 °C	12 g/10 min @Load 2.65 lb, Temperature 572 °F	[cm ³ /10 min] Melt Volume Rate; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, H358/30	95.0 MPa	13800 psi	ISO 2039-1
Tensile Strength at Break	50.0 MPa	7250 psi	50 mm/min; ISO 527
Tensile Strength, Yield	63.0 MPa	9140 psi	50 mm/min; ISO 527
Elongation at Break	50 %	50 %	50 mm/min; ISO 527
Elongation at Yield	6.0 %	6.0 %	50 mm/min; ISO 527
Tensile Modulus	2.35 GPa	341 ksi	1 mm/min; ISO 527
Flexural Yield Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
Flexural Modulus	2.30 GPa	334 ksi	2 mm/min; ISO 178

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 µm/m-°C @Temperature 23.0 - 80.0 °C	38.9 µin/in-°F @Temperature 73.4 - 176 °F	ISO 11359-2
Deflection Temperature at 0.46 MPa (66 psi)	135 °C	275 °F	Edgew 120*10*4 sp=100mm; ISO 75/Be

Thermal Properties	Metric	English	Comments
Dimensional Temperature at 1.8 MPa (264 psi)	124 °C	255 °F	COGEM 120*10*4 sp=100mm; ISO 75/Ae
Vicat Softening Point	141 °C	286 °F	Rate B/50; ISO 306
	142 °C	288 °F	Rate B/120; ISO 306
Flammability, UL94	V-2 @Thickness 1.50 mm	V-2 @Thickness 0.0591 in	UL 94 by SABIC-IP
	V-0 @Thickness 3.00 mm	V-0 @Thickness 0.118 in	UL 94 by SABIC-IP

Optical Properties	Metric	English	Comments
Transmission, Visible	80 %	80 %	transparent/translucent; thickness not quantified

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	PASSES	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China