

SABIC Innovative Plastics Lexan® HF1130 PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

UV-stabilized. Good clarity, heat resistance, property retention and dimensional stability.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-HF1130-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	25 g/10 min @Load 1.20 kg, Temperature 300 °C	25 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	65.0 MPa	9430 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	62.0 MPa	8990 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	110 %	110 %	Type I, 50 mm/min; ASTM D638
Flexural Yield Strength	93.0 MPa	13500 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.30 GPa	334 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	6.40 J/cm	12.0 ft-lb/in	ASTM D256
Tensile Impact Strength	378 kJ/m ²	180 ft-lb/in ²	Type S; ASTM D1822
Dart Drop, Total Energy	54.0 J	39.8 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	126 °C @Thickness 6.40 mm	259 °F @Thickness 0.252 in	unannealed; ASTM D648
UL RTI, Electrical	100 °C	212 °F	UL 746B
UL RTI, Mechanical with Impact	100 °C	212 °F	UL 746B
UL RTI, Mechanical without Impact	100 °C	212 °F	UL 746B

Thermal Properties	V-2 Metric	V-2 English	Comments
	@Thickness 1.47 mm	@Thickness 0.0579 in	

Optical Properties	Metric	English	Comments
Haze	1.0 % @Thickness 2.54 mm	1.0 % @Thickness 0.100 in	ASTM D1003
Transmission, Visible	88 %	88 %	2.54 mm; ASTM D1003

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China