

## SABIC Innovative Plastics Lexan® HPH4704 PPC

Category : Polymer , Thermoplastic , Polyphthalate Carbonate

### Material Notes:

High heat specialty polycarbonate. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO10993 or USP Class VI). EtO, steam, gamma and e-beam sterilizable.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Lexan-HPH4704-PPC.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-HPH4704-PPC.php)

| Physical Properties            | Metric                                               | English                                              | Comments                                |
|--------------------------------|------------------------------------------------------|------------------------------------------------------|-----------------------------------------|
| Specific Gravity               | 1.20 g/cc                                            | 1.20 g/cc                                            | ASTM D792                               |
| Density                        | 1.19 g/cc                                            | 0.0430 lb/in <sup>3</sup>                            | ASTM D792                               |
|                                | 1.20 g/cc                                            | 0.0434 lb/in <sup>3</sup>                            | ISO 1183                                |
| Water Absorption               | 0.19 %<br>@Time 86400 sec                            | 0.19 %<br>@Time 24.0 hour                            | ASTM D570                               |
| Moisture Absorption            | 0.350 %                                              | 0.350 %                                              | 23°C / 50% RH; ISO 62                   |
| Water Absorption at Saturation | 0.16 %                                               | 0.16 %                                               | ISO 62                                  |
| Linear Mold Shrinkage, Flow    | 0.0080 - 0.010 cm/cm<br>@Thickness 3.20 mm           | 0.0080 - 0.010 in/in<br>@Thickness 0.126 in          | SABIC Method                            |
| Melt Flow                      | 2.0 g/10 min<br>@Load 1.20 kg,<br>Temperature 300 °C | 2.0 g/10 min<br>@Load 2.65 lb,<br>Temperature 572 °F | ASTM D1238                              |
| Melt Index of Compound         | 2.0 g/10 min<br>@Load 1.20 kg,<br>Temperature 300 °C | 2.0 g/10 min<br>@Load 2.65 lb,<br>Temperature 572 °F | MVR [cm <sup>3</sup> /10 min]; ISO 1133 |

| Mechanical Properties     | Metric   | English   | Comments                     |
|---------------------------|----------|-----------|------------------------------|
| Hardness, Rockwell M      | 92       | 92        | ASTM D785                    |
| Hardness, Rockwell R      | 127      | 127       | ASTM D785                    |
| Tensile Strength at Break | 68.0 MPa | 9860 psi  | 50 mm/min; ISO 527           |
|                           | 77.0 MPa | 11200 psi | Type I, 50 mm/min; ASTM D638 |
| Tensile Strength, Yield   | 65.0 MPa | 9430 psi  | Type I, 50 mm/min; ASTM D638 |
|                           | 68.0 MPa | 9860 psi  | 50 mm/min; ISO 527           |
| Elongation at Break       | 78 %     | 78 %      | Type I, 50 mm/min; ASTM D638 |

| Mechanical Properties      | Metric                  | English                    | Comments                           |
|----------------------------|-------------------------|----------------------------|------------------------------------|
|                            | 102 %                   | 102 %                      | 50 mm/min; ISO 527                 |
| Elongation at Yield        | 7.0 %                   | 7.0 %                      | 50 mm/min; ISO 527                 |
|                            | 8.0 %                   | 8.0 %                      | Type I, 50 mm/min; ASTM D638       |
| Tensile Modulus            | 2.10 GPa                | 305 ksi                    | 5 mm/min; ASTM D638                |
|                            | 2.17 GPa                | 315 ksi                    | 1 mm/min; ISO 527                  |
| Flexural Yield Strength    | 66.0 MPa                | 9570 psi                   | 2 mm/min; ISO 178                  |
|                            | 97.0 MPa                | 14100 psi                  | 1.3 mm/min, 50 mm span; ASTM D790  |
| Flexural Modulus           | 2.07 GPa                | 300 ksi                    | 2 mm/min; ISO 178                  |
|                            | 2.33 GPa                | 338 ksi                    | 1.3 mm/min, 50 mm span; ASTM D790  |
| Izod Impact, Notched       | 3.70 J/cm               | 6.93 ft-lb/in              | ASTM D256                          |
|                            | 0.840 J/cm              | 1.57 ft-lb/in              | ASTM D256                          |
|                            | @Temperature -30.0 °C   | @Temperature -22.0 °F      |                                    |
| Izod Impact, Unnotched     | 32.0 J/cm               | 59.9 ft-lb/in              | ASTM D4812                         |
| Izod Impact, Notched (ISO) | 7.00 kJ/m <sup>2</sup>  | 3.33 ft-lb/in <sup>2</sup> | 80*10*4; ISO 180/1A                |
|                            | 6.00 kJ/m <sup>2</sup>  | 2.86 ft-lb/in <sup>2</sup> | 80*10*4; ISO 180/1A                |
|                            | @Temperature -30.0 °C   | @Temperature -22.0 °F      |                                    |
| Charpy Impact, Notched     | 0.900 J/cm <sup>2</sup> | 4.28 ft-lb/in <sup>2</sup> | Edgew 80*10*4 sp=62mm; ISO 179/1eA |
| Tensile Impact Strength    | 577 kJ/m <sup>2</sup>   | 275 ft-lb/in <sup>2</sup>  | Type S; ASTM D1822                 |
| Dart Drop, Total Energy    | 149 J                   | 110 ft-lb                  | ASTM D3029                         |
|                            | 74.0 J                  | 54.6 ft-lb                 | ASTM D3763                         |
|                            | @Temperature 23.0 °C    | @Temperature 73.4 °F       |                                    |

| Thermal Properties            | Metric                       | English                     | Comments    |
|-------------------------------|------------------------------|-----------------------------|-------------|
| CTE, linear, Parallel to Flow | 60.0 µm/m-°C                 | 33.3 µin/in-°F              | ASTM E 831  |
|                               | @Temperature -40.0 - 40.0 °C | @Temperature -40.0 - 104 °F |             |
|                               | 60.0 µm/m-°C                 | 33.3 µin/in-°F              | ISO 11359-2 |
|                               | @Temperature -40.0 - 40.0 °C | @Temperature -40.0 - 104 °F |             |

| Thermal Properties<br>CTE, linear, Transverse to Flow | 60.0 µm/m-°C<br>Metric       | 33.3 µin/in-°F<br>English   | Comments<br>ASTM E 831           |
|-------------------------------------------------------|------------------------------|-----------------------------|----------------------------------|
|                                                       | @Temperature -40.0 - 40.0 °C | @Temperature -40.0 - 104 °F |                                  |
|                                                       | 60.0 µm/m-°C                 | 33.3 µin/in-°F              | ISO 11359-2                      |
|                                                       | @Temperature -40.0 - 40.0 °C | @Temperature -40.0 - 104 °F |                                  |
| Specific Heat Capacity                                | 1.25 J/g-°C                  | 0.299 BTU/lb-°F             | ASTM C351                        |
| Thermal Conductivity                                  | 0.210 W/m-K                  | 1.46 BTU-in/hr-ft²-°F       | ASTM C177                        |
| Deflection Temperature at 1.8 MPa (264 psi)           | 150 °C                       | 302 °F                      | Flatw 80*10*4 sp=64mm; ISO 75/Af |
|                                                       | 148 °C                       | 298 °F                      | unannealed; ASTM D648            |
|                                                       | @Thickness 3.20 mm           | @Thickness 0.126 in         |                                  |
| Vicat Softening Point                                 | 165 °C                       | 329 °F                      | Rate B/50; ISO 306               |
|                                                       | 167 °C                       | 333 °F                      | Rate B/120; ISO 306              |
|                                                       | 173 °C                       | 343 °F                      | Rate B/50; ASTM D1525            |
| UL RTI, Electrical                                    | 130 °C                       | 266 °F                      | UL 746B                          |
| UL RTI, Mechanical with Impact                        | 130 °C                       | 266 °F                      | UL 746B                          |
| UL RTI, Mechanical without Impact                     | 130 °C                       | 266 °F                      | UL 746B                          |
| Flammability, UL94                                    | HB                           | HB                          | UL 94                            |
|                                                       | @Thickness 1.47 mm           | @Thickness 0.0579 in        |                                  |

| Optical Properties    | Metric             | English             | Comments            |
|-----------------------|--------------------|---------------------|---------------------|
| Refractive Index      | 1.60               | 1.60                | ASTM D542           |
| Haze                  | 1.0 %              | 1.0 %               | ASTM D1003          |
|                       | @Thickness 2.54 mm | @Thickness 0.100 in |                     |
| Transmission, Visible | 85 %               | 85 %                | 2.54 mm; ASTM D1003 |

| Electrical Properties | Metric                | English               | Comments  |
|-----------------------|-----------------------|-----------------------|-----------|
| Volume Resistivity    | >= 2.50e+17 ohm-cm    | >= 2.50e+17 ohm-cm    | ASTM D257 |
| Dielectric Constant   | 3.1                   | 3.1                   | ASTM D150 |
|                       | @Frequency 1.00e+6 Hz | @Frequency 1.00e+6 Hz |           |
|                       | 3.27                  | 3.27                  |           |

| Electrical Properties                | Metric                              | English                             | ASTM D150<br>Comments |
|--------------------------------------|-------------------------------------|-------------------------------------|-----------------------|
|                                      | @Frequency 50.0 - 60.0 Hz           | @Frequency 50.0 - 60.0 Hz           |                       |
| Dielectric Strength                  | 20.0 kV/mm<br>@Thickness 3.20 mm    | 508 kV/in<br>@Thickness 0.126 in    | in air; ASTM D149     |
| Dissipation Factor                   | 0.0016<br>@Frequency 50.0 - 60.0 Hz | 0.0016<br>@Frequency 50.0 - 60.0 Hz | ASTM D150             |
|                                      | 0.026<br>@Frequency 100 Hz          | 0.026<br>@Frequency 100 Hz          | ASTM D150             |
| Arc Resistance                       | 60 - 120 sec                        | 60 - 120 sec                        | Tungsten; ASTM D495   |
| Comparative Tracking Index           | 175 - 250 V                         | 175 - 250 V                         | UL 746A               |
| Hot Wire Ignition, HWI               | 30 - 60 sec                         | 30 - 60 sec                         | UL 746A               |
| High Amp Arc Ignition, HAI           | 15 - 30 arcs                        | 15 - 30 arcs                        | UL 746A               |
| High Voltage Arc-Tracking Rate, HVTR | 80.0 - 150 mm/min                   | 3.15 - 5.91 in/min                  | UL 746A               |

| Descriptive Properties | Value                  | Comments  |
|------------------------|------------------------|-----------|
| Specific Volume        | 0.83cm <sup>3</sup> /g | ASTM D792 |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China