

SABIC Innovative Plastics Lexan® LS2 PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Automotive lens applications. Medium viscosity. UV-stabilized. Transparent colors only.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-LS2-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Water Absorption	0.15 % @Time 86400 sec	0.15 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	11 g/10 min @Load 1.20 kg, Temperature 300 °C	11 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	62.0 MPa	8990 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	130 %	130 %	Type I, 50 mm/min; ASTM D638
Flexural Yield Strength	96.0 MPa	13900 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.34 GPa	339 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	8.01 J/cm	15.0 ft-lb/in	ASTM D256
Tensile Impact Strength	577 kJ/m ²	275 ft-lb/in ²	Type S; ASTM D1822
Dart Drop, Total Energy	63.0 J	46.5 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763
	169 J	125 ft-lb	SABIC Method

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	132 °C @Thickness 6.40 mm	270 °F @Thickness 0.252 in	unannealed; ASTM D648
UL RTI, Electrical	100 °C	212 °F	UL 746B

UL RTI, Mechanical with Impact Thermal Properties	100 °C Metric	212 °F English	UL 746B Comments
UL RTI, Mechanical without Impact	100 °C	212 °F	UL 746B
Flammability, UL94	HB @Thickness 1.47 mm	HB @Thickness 0.0579 in	UL 94

Optical Properties	Metric	English	Comments
Transmission, Visible	88 %	88 %	2.54 mm; ASTM D1003

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	250 - 400 V	250 - 400 V	UL 746A
Hot Wire Ignition, HWI	7.0 - 15 sec	7.0 - 15 sec	UL 746A
High Amp Arc Ignition, HAI	60 - 120 arcs	60 - 120 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	25.4 - 80.0 mm/min	1.00 - 3.15 in/min	UL 746A

Descriptive Properties	Value	Comments
UV-light, water exposure/immersion	F1	UL 746C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China