

SABIC Innovative Plastics Lexan® LUX2619 PC

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Lexan® LUX2619 Polycarbonate resin is an extrusion grade. It is UL94 V-2 rated at 1.5 mm. It was designed for high light reflectance.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-LUX2619-PC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.34 g/cc	1.34 g/cc	ASTM D792
Density	1.34 g/cc	0.0484 lb/in ³	ISO 1183
Moisture Absorption	0.150 %	0.150 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.35 %	0.35 %	ISO 62
Linear Mold Shrinkage, Flow	0.0080 - 0.010 cm/cm @Thickness 3.20 mm	0.0080 - 0.010 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	7.5 g/10 min @Load 1.20 kg, Temperature 300 °C	7.5 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	50.0 MPa	7250 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	57.0 MPa	8270 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	74 %	74 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	6.0 %	6.0 %	Type I, 50 mm/min; ASTM D638
Flexural Yield Strength	97.0 MPa	14100 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.73 GPa	396 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	6.40 J/cm	12.0 ft-lb/in	ASTM D256
	1.35 J/cm @Temperature -30.0 °C	2.53 ft-lb/in @Temperature -22.0 °F	ASTM D256
Izod Impact, Unnotched	21.3 J/cm	39.9 ft-lb/in	ASTM D4812
Dart Drop, Total Energy	69.0 J @Temperature 23.0 °C	50.9 ft-lb @Temperature 73.4 °F	ASTM D3763

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	61.0 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	33.9 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	ASTM E 831
	@Temperature -40.0 - 40.0 $^{\circ}\text{C}$	@Temperature -40.0 - 104 $^{\circ}\text{F}$	
CTE, linear, Transverse to Flow	64.0 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	35.6 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	ASTM E 831
	@Temperature -40.0 - 40.0 $^{\circ}\text{C}$	@Temperature -40.0 - 104 $^{\circ}\text{F}$	
Deflection Temperature at 0.46 MPa (66 psi)	141 $^{\circ}\text{C}$	286 $^{\circ}\text{F}$	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	129 $^{\circ}\text{C}$	264 $^{\circ}\text{F}$	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	147 $^{\circ}\text{C}$	297 $^{\circ}\text{F}$	Rate B/50; ASTM D1525
Flammability, UL94	V-2	V-2	UL 94
	@Thickness 1.50 mm	@Thickness 0.0591 in	
Glow Wire Test	850 $^{\circ}\text{C}$	1560 $^{\circ}\text{F}$	IEC 60695-2-13
	875 $^{\circ}\text{C}$	1610 $^{\circ}\text{F}$	IEC 60695-2-13
	960 $^{\circ}\text{C}$	1760 $^{\circ}\text{F}$	IEC 60695-2-12
	@Thickness 1.00 - 3.00 mm	@Thickness 0.0394 - 0.118 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China