

SABIC Innovative Plastics Lexan® OQ1023 PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Lexan OQ1023 resin is an optical high purity PC resin optimized for demanding recordable and rewritable formats (CD-R, DVD-R, DVD-RW).

It is also suitable for short cycletime CD and DVD production

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-OQ1023-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Moisture Absorption	0.150 %	0.150 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.35 %	0.35 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	on Tensile Bar; SABIC Method
Melt Index of Compound	8.0 g/10 min @Load 1.20 kg, Temperature 250 °C	8.0 g/10 min @Load 2.65 lb, Temperature 482 °F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, H358/30	100 MPa	14500 psi	ISO 2039-1
Tensile Strength at Break	45.0 MPa	6530 psi	50 mm/min; ISO 527
Tensile Strength, Yield	60.0 MPa	8700 psi	50 mm/min; ISO 527
Elongation at Break	>= 40 %	>= 40 %	50 mm/min; ISO 527
Elongation at Yield	6.0 %	6.0 %	50 mm/min; ISO 527
Tensile Modulus	2.35 GPa	341 ksi	1 mm/min; ISO 527
Flexural Yield Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
Flexural Modulus	2.35 GPa	341 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	9.00 kJ/m ²	4.28 ft-lb/in ²	80*10*4; ISO 180/1A
	15.0 kJ/m ²	7.14 ft-lb/in ²	80*10*3; ISO 180/1A
	3.00 kJ/m ² @Temperature -30.0 °C	1.43 ft-lb/in ² @Temperature -22.0 °F	80*10*4; ISO 180/1A
	12.0 kJ/m ² @Temperature -30.0 °C	5.71 ft-lb/in ² @Temperature -22.0 °F	80*10*3; ISO 180/1A

Mechanical Properties	Metric	English	Comments
ISO Impact, Unnotched (ISO)	NB	NB	80*10*4; ISO 180/1U
	NB	NB	80*10*4; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	NB	NB	80*10*3; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*4 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*4 sp=62mm; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.800 J/cm²	3.81 ft-lb/in²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
	4.00 J/cm²	19.0 ft-lb/in²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	1.20 J/cm²	5.71 ft-lb/in²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 µm/m-°C	38.9 µin/in-°F	ISO 11359-2
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	
CTE, linear, Transverse to Flow	70.0 µm/m-°C	38.9 µin/in-°F	ISO 11359-2
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft²-°F	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	132 °C	270 °F	Edgew 120*10*4 sp=100mm; ISO 75/Be
Deflection Temperature at 1.8 MPa (264 psi)	124 °C	255 °F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
Vicat Softening Point	138 °C	280 °F	Rate B/50; ISO 306
	140 °C	284 °F	Rate B/120; ISO 306

Optical Properties	Metric	English	Comments
Refractive Index	1.586	1.586	ISO 489
Haze	<= 0.70 % @Thickness 2.54 mm	<= 0.70 % @Thickness 0.100 in	ASTM D1003
Transmission, Visible	>= 90 %	>= 90 %	2.54 mm; ASTM D1003

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	ROA; IEC 60093
Dielectric Constant	2.7 @Frequency 1.00e+6 Hz	2.7 @Frequency 1.00e+6 Hz	IEC 60250
Dielectric Strength	17.0 kV/mm @Thickness 3.20 mm	432 kV/in @Thickness 0.126 in	in oil; IEC 60243-1
Dissipation Factor	0.010 @Frequency 1.00e+6 Hz	0.010 @Frequency 1.00e+6 Hz	IEC 60250

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	PASSES	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China