

SABIC Innovative Plastics Lexan® XHT2146 PC Copolymer

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

XHT2146 resin is a high flow, high heat polycarbonate copolymer with improved release performance compared to Lexan® XHT2141 resin. It is available in a range of opaque and limited transparent colors.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-XHT2146-PC-Copolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Moisture Absorption	0.230 %	0.230 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.30 %	0.30 %	ISO 62
Linear Mold Shrinkage, Flow	0.0060 - 0.0090 cm/cm @Thickness 3.20 mm	0.0060 - 0.0090 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	46 g/10 min @Load 2.16 kg, Temperature 330 °C	46 g/10 min @Load 4.76 lb, Temperature 626 °F	ASTM D1238
Melt Index of Compound	43 g/10 min @Load 2.16 kg, Temperature 330 °C	43 g/10 min @Load 4.76 lb, Temperature 626 °F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	60.0 MPa	8700 psi	Type I, 50 mm/min; ASTM D638
	60.0 MPa	8700 psi	50 mm/min; ISO 527
Tensile Strength, Yield	70.0 MPa	10200 psi	Type I, 50 mm/min; ASTM D638
	70.0 MPa	10200 psi	50 mm/min; ISO 527
Elongation at Break	90 %	90 %	Type I, 50 mm/min; ASTM D638
	90 %	90 %	50 mm/min; ISO 527
Elongation at Yield	6.5 %	6.5 %	Type I, 50 mm/min; ASTM D638
	6.5 %	6.5 %	50 mm/min; ISO 527
Tensile Modulus	2.60 GPa	377 ksi	5 mm/min; ASTM D638

Mechanical Properties	2.60 GPa Metric	377 ksi English	1 mm/min; ISO 527 Comments
Flexural Yield Strength	100 MPa	14500 psi	2 mm/min; ISO 178
	110 MPa	16000 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.45 GPa	355 ksi	2 mm/min; ISO 178
	2.55 GPa	370 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	1.15 J/cm	2.15 ft-lb/in	ASTM D256
	0.750 J/cm	1.41 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Notched (ISO)	10.0 kJ/m ²	4.76 ft-lb/in ²	80*10*3; ISO 180/1A
	9.00 kJ/m ²	4.28 ft-lb/in ²	80*10*3; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	NB	NB	80*10*3; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.20 J/cm ²	5.71 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	0.900 J/cm ²	4.28 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Dart Drop, Total Energy	68.0 J	50.2 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	60.0 µm/m-°C	33.3 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	60.0 µm/m-°C	33.3 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	

Thermal Properties CTE, linear, transverse to Flow	60.0 µm/m-°C Metric	33.3 µin/in-°F English	Comments ASTM E-831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	60.0 µm/m-°C	33.3 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Deflection Temperature at 0.46 MPa (66 psi)	155 °C	311 °F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	142 °C	288 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	145 °C	293 °F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	160 °C	320 °F	Rate B/50; ISO 306
	161 °C	322 °F	Rate B/50; ASTM D1525
	162 °C	324 °F	Rate B/120; ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China