

SABIC Innovative Plastics NORYL APS430 PPE+PPS (Asia Pacific)

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polyphenylene Sulfide (PPS)

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-APS430-PPEPPS-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.48 g/cc	1.48 g/cc	ASTM D792
Water Absorption	0.020 % @Time 86400 sec	0.020 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0030 - 0.0070 cm/cm @Thickness 3.20 mm	0.0030 - 0.0070 in/in @Thickness 0.126 in	SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	122 MPa	17700 psi	SABIC - Japan Method
Elongation at Break	10 %	10 %	SABIC - Japan Method
Flexural Strength	166 MPa	24100 psi	ASTM D790
Flexural Modulus	8.62 GPa	1250 ksi	ASTM D790
Izod Impact, Notched	0.780 J/cm	1.46 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	18.0 - 58.0 Åµm/m-Å°C @Temperature -30.0 - 30.0 Å°C	10.0 - 32.2 Åµin/in-Å°F @Temperature -22.0 - 86.0 Å°F	TMA
Deflection Temperature at 0.46 MPa (66 psi)	255 Å°C @Thickness 3.20 mm	491 Å°F @Thickness 0.126 in	unannealed; ASTM D648
Flammability, UL94	V-0 @Thickness 0.800 mm	V-0 @Thickness 0.0315 in	UL 94

Electrical Properties	Metric	English	Comments
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	ASTM D257
Dielectric Constant	3.3 @Frequency 50.0 - 60.0 Hz	3.3 @Frequency 50.0 - 60.0 Hz	ASTM D150

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China