

SABIC Innovative Plastics NORYL GTX GTX4610 PPE+PA (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Nylon , Polyphenylene Ether/PPO

Material Notes:

Noryl GTX* GTX4610 resin is a high performance, 10% glass filled blend of PPE/PA that exhibits an excellent balance of non-halogenated flame retardance, dimensional stability, high heat resistance, strength, and flow. The material is available in limited colors for injection molding.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-GTX-GTX4610-PPEPA-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.21 g/cc	1.21 g/cc	ASTM D792
Density	1.21 g/cc	0.0437 lb/in ³	ISO 1183
Moisture Absorption	0.500 %	0.500 %	23Â°C / 50% RH; ISO 62
Water Absorption at Saturation	3.8 %	3.8 %	ISO 62
Linear Mold Shrinkage, Flow	0.0088 - 0.0094 cm/cm @Thickness 3.20 mm	0.0088 - 0.0094 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0095 - 0.0101 cm/cm @Thickness 3.20 mm	0.0095 - 0.0101 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	18 g/10 min @Load 5.00 kg, Temperature 300 Â°C	18 g/10 min @Load 11.0 lb, Temperature 572 Â°F	ASTM D1238
Melt Index of Compound	15 g/10 min @Load 5.00 kg, Temperature 300 Â°C	15 g/10 min @Load 11.0 lb, Temperature 572 Â°F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	88.0 MPa	12800 psi	Type I, 5 mm/min; ASTM D638
	88.0 MPa	12800 psi	5 mm/min; ISO 527
Tensile Strength, Yield	88.0 MPa	12800 psi	Type I, 5 mm/min; ASTM D638
	88.0 MPa	12800 psi	5 mm/min; ISO 527
Elongation at Break	7.0 %	7.0 %	Type I, 5 mm/min; ASTM D638
	7.0 %	7.0 %	5 mm/min; ISO 527

Elongation at Yield Mechanical Properties	3.0 % Metric	3.0 % English	Type I, 5 mm/min; ASTM D638 Comments
	3.0 %	3.0 %	5 mm/min; ISO 527
Tensile Modulus	5.00 GPa	725 ksi	5 mm/min; ASTM D638
	5.00 GPa	725 ksi	1 mm/min; ISO 527
Flexural Yield Strength	145 MPa	21000 psi	1.3 mm/min, 50 mm span; ASTM D790
	145 MPa	21000 psi	2 mm/min; ISO 178
Flexural Modulus	4.60 GPa	667 ksi	1.3 mm/min, 50 mm span; ASTM D790
	4.60 GPa	667 ksi	2 mm/min; ISO 178
Izod Impact, Notched	0.800 J/cm	1.50 ft-lb/in	ASTM D256
	0.650 J/cm	1.22 ft-lb/in	ASTM D256
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Izod Impact, Notched (ISO)	7.00 kJ/mÂ²	3.33 ft-lb/inÂ²	80*10*4; ISO 180/1A
	5.00 kJ/mÂ²	2.38 ft-lb/inÂ²	80*10*4; ISO 180/1A
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Charpy Impact, Notched	0.700 J/cmÂ²	3.33 ft-lb/inÂ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
Dart Drop, Total Energy	12.0 J	8.85 ft-lb	ASTM D3763
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	41.0 Âµm/m-Â°C	22.8 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
	41.0 Âµm/m-Â°C	22.8 Âµin/in-Â°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
CTE, linear, Transverse to Flow	74.0 Âµm/m-Â°C	41.1 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
	74.0 Âµm/m-Â°C	41.1 Âµin/in-Â°F	ISO 11359-2
	@Temperature -40.0 -	@Temperature -40.0 -	

Thermal Properties	40.0 Â°C Metric	104 Â°F English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	224 Â°C	435 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	220 Â°C	428 Â°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	218 Â°C	424 Â°F	Rate B/50; ASTM D1525
	218 Â°C	424 Â°F	Rate B/50; ISO 306
	220 Â°C	428 Â°F	Rate B/120; ISO 306
Flammability, UL94	V-1	V-1	UL 94 by SABIC-IP
	@Thickness 0.800 mm	@Thickness 0.0315 in	
	5VB	5VB	UL 94 by SABIC-IP
	@Thickness 2.00 mm	@Thickness 0.0787 in	
	5VA	5VA	UL 94 by SABIC-IP
	@Thickness 2.00 mm	@Thickness 0.0787 in	
Glow Wire Test	825 Â°C	1520 Â°F	IEC 60695-2-13
	960 Â°C	1760 Â°F	IEC 60695-2-12
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Strength	23.2 kV/mm	589 kV/in	in air; ASTM D149
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	24.4 kV/mm	620 kV/in	in oil; ASTM D149
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Comparative Tracking Index	425 V	425 V	IEC 60112
	400 - 600 V	400 - 600 V	UL 746A
High Amp Arc Ignition, HAI	>= 120 arcs	>= 120 arcs	UL 746A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China