

SABIC Innovative Plastics NORYL GTX GTX909 PPE+PS+PA (Asia Pacific)

Category : Polymer , Thermoplastic , Nylon , Polyphenylene Ether/PPO , Polystyrene (PS)

Material Notes:

400F (205C) HDT. 3.3 Notched Izod. Excellent chemical resistance

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-GTX-GTX909-PPEPSA-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.13 g/cc	1.13 g/cc	ASTM D792
Water Absorption	0.54 % @Time 86400 sec	0.54 % @Time 24.0 hour	ASTM D570
Moisture Absorption at Equilibrium	4.4 %	4.4 %	ASTM D570
Linear Mold Shrinkage, Flow	0.013 - 0.017 cm/cm @Thickness 3.20 mm	0.013 - 0.017 in/in @Thickness 0.126 in	SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	59.0 MPa	8560 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	66.0 MPa	9570 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	50 %	50 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	9.0 %	9.0 %	Type I, 50 mm/min; ASTM D638
Flexural Yield Strength	99.0 MPa	14400 psi	2.6 mm/min, 100 mm span; ASTM D790
Flexural Modulus	2.37 GPa	344 ksi	2.6 mm/min, 100 mm span; ASTM D790
Izod Impact, Notched	1.76 J/cm	3.30 ft-lb/in	ASTM D256
	1.06 J/cm @Temperature -30.0 Â°C	1.99 ft-lb/in @Temperature -22.0 Â°F	ASTM D256
Dart Drop, Total Energy	40.0 J	29.5 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763
	24.0 J @Temperature -30.0 Â°C	17.7 ft-lb @Temperature -22.0 Â°F	Instrumented Impact Energy @ peak; ASTM D3763

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	95.4 Âµm/m-Â°C @Temperature -20.0 - 150 Â°C	53.0 Âµin/in-Â°F @Temperature -4.00 - 302 Â°F	ASTM E 831
CTE, linear, Transverse to Flow	81.0 Âµm/m-Â°C @Temperature -20.0 - 150 Â°C	45.0 Âµin/in-Â°F @Temperature -4.00 - 302 Â°F	ASTM E 831
Deflection Temperature at 0.46 MPa (66 psi)	204 Â°C @Thickness 6.40 mm	399 Â°F @Thickness 0.252 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	125 Â°C @Thickness 6.40 mm	257 Â°F @Thickness 0.252 in	unannealed; ASTM D648
Vicat Softening Point	245 Â°C	473 Â°F	Rate B/50; ASTM D1525

Electrical Properties	Metric	English	Comments
Volume Resistivity	4.40e+16 ohm-cm	4.40e+16 ohm-cm	ASTM D257
Surface Resistance	1.70e+16 ohm	1.70e+16 ohm	ASTM D257
Dielectric Constant	2.76 @Frequency 1.00e+6 Hz	2.76 @Frequency 1.00e+6 Hz	ASTM D150
	3.27 @Frequency 50.0 - 60.0 Hz	3.27 @Frequency 50.0 - 60.0 Hz	ASTM D150
Dielectric Strength	25.5 kV/mm @Thickness 3.20 mm	648 kV/in @Thickness 0.126 in	in oil; ASTM D149
Dissipation Factor	0.019 @Frequency 1.00e+6 Hz	0.019 @Frequency 1.00e+6 Hz	ASTM D150
	0.039 @Frequency 50.0 - 60.0 Hz	0.039 @Frequency 50.0 - 60.0 Hz	ASTM D150

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China