

SABIC Innovative Plastics NORYL INT1512 PPE+HIPS (Asia Pacific)

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polystyrene (PS)

Material Notes:

PPE/HIPS GF filled for auto interior

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-INT1512-PPEHIPS-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.12 g/cc	1.12 g/cc	ASTM D792
Water Absorption	0.060 % @Time 86400 sec	0.060 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0040 - 0.0060 cm/cm @Thickness 3.20 mm	0.0040 - 0.0060 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	39.3 g/10 min @Load 10.0 kg, Temperature 250 Â°C	39.3 g/10 min @Load 22.0 lb, Temperature 482 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	70.0 MPa	10200 psi	SABIC - Japan Method
Elongation at Break	10 %	10 %	SABIC - Japan Method
Flexural Strength	101 MPa	14600 psi	ASTM D790
Flexural Modulus	3.82 GPa	554 ksi	ASTM D790
Izod Impact, Notched	0.980 J/cm	1.84 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	50.0 Âµm/m-Â°C @Temperature -30.0 - 30.0 Â°C	27.8 Âµin/in-Â°F @Temperature -22.0 - 86.0 Â°F	TMA
Deflection Temperature at 1.8 MPa (264 psi)	118 Â°C @Thickness 6.40 mm	244 Â°F @Thickness 0.252 in	unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China