

SABIC Innovative Plastics NORYL N110 PPE+HIPS (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polystyrene (PS)

Material Notes:

NORYL N110 is an unfilled material, with a Vicat B/120 of 115 Å°C according ISO 306. NORYL N110 has medium temperature resistance and good

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-N110-PPEHIPS-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in ³	ISO 1183
Moisture Absorption	0.0700 %	0.0700 %	23Å°C / 50% RH; ISO 62
Water Absorption at Saturation	0.20 %	0.20 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	on Tensile Bar; SABIC Method
Melt Index of Compound	15 g/10 min @Load 3.80 kg, Temperature 280 Å°C	15 g/10 min @Load 8.38 lb, Temperature 536 Å°F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, H358/30	95.0 MPa	13800 psi	ISO 2039-1
Tensile Strength at Break	40.0 MPa	5800 psi	50 mm/min; ISO 527
Tensile Strength, Yield	45.0 MPa	6530 psi	50 mm/min; ISO 527
Elongation at Break	30 %	30 %	50 mm/min; ISO 527
Elongation at Yield	3.0 %	3.0 %	50 mm/min; ISO 527
Tensile Modulus	2.20 GPa	319 ksi	1 mm/min; ISO 527
Flexural Yield Strength	60.0 MPa	8700 psi	2 mm/min; ISO 178
Flexural Modulus	2.00 GPa	290 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	11.0 kJ/m ²	5.23 ft-lb/in ²	80*10*4; ISO 180/1A
	5.00 kJ/m ² @Temperature -30.0 Å°C	2.38 ft-lb/in ² @Temperature -22.0 Å°F	80*10*4; ISO 180/1A
Charpy Impact, Notched	1.10 J/cm ²	5.23 ft-lb/in ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
	0.500 J/cm ²	2.38 ft-lb/in ²	

Mechanical Properties	Metric	English	Comments
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	Edgew 80*10*4 sp=62mm; ISO 11359-2

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 Âµm/m-Â°C @Temperature 23.0 - 80.0 Â°C	38.9 Âµin/in-Â°F @Temperature 73.4 - 176 Â°F	ISO 11359-2
CTE, linear, Transverse to Flow	90.0 Âµm/m-Â°C @Temperature 23.0 - 80.0 Â°C	50.0 Âµin/in-Â°F @Temperature 73.4 - 176 Â°F	ISO 11359-2
Thermal Conductivity	0.220 W/m-K	1.53 BTU-in/hr-ftÂ²-Â°F	ISO 8302
Hot Ball Pressure Test	<= 115 Â°C	<= 239 Â°F	IEC 60695-10-2
Deflection Temperature at 0.46 MPa (66 psi)	105 Â°C	221 Â°F	Edgew 120*10*4 sp=100mm; ISO 75/Be
Deflection Temperature at 1.8 MPa (264 psi)	95.0 Â°C	203 Â°F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
Vicat Softening Point	115 Â°C	239 Â°F	Rate B/50; ISO 306
	115 Â°C	239 Â°F	Rate B/120; ISO 306
	120 Â°C	248 Â°F	Rate A/50; ISO 306
UL RTI, Electrical	90.0 Â°C	194 Â°F	UL 746B
UL RTI, Mechanical with Impact	85.0 Â°C	185 Â°F	UL 746B
UL RTI, Mechanical without Impact	95.0 Â°C	203 Â°F	UL 746B
Flammability, UL94	HB @Thickness 3.00 mm	HB @Thickness 0.118 in	UL 94
	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	UL 94
Oxygen Index	19 %	19 %	ISO 4589
Glow Wire Test	960 Â°C @Thickness 3.20 mm	1760 Â°F @Thickness 0.126 in	IEC 60695-2-12

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	ROA; IEC 60093

Electrical Properties	Metric	English	Comments
Dielectric Constant	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	IEC 60250
	2.6	2.6	IEC 60250
Dielectric Strength	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	IEC 60250
	19.0 kV/mm	483 kV/in	in oil; IEC 60243-1
Dissipation Factor	@Thickness 3.20 mm	@Thickness 0.126 in	
	0.0010	0.0010	
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	IEC 60250
	0.0040	0.0040	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	IEC 60250

Descriptive Properties	Value	Comments
Ball Pressure Test, 75Â°C +/- 2Â°C	PASSES	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China