

SABIC Innovative Plastics NORYL PX1543 PPE+PS (Asia Pacific)

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polystyrene (PS)

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-PX1543-PPEPS-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.06 g/cc	1.06 g/cc	ASTM D792
Water Absorption	0.066 % @Time 86400 sec	0.066 % @Time 24.0 hour	ASTM D570

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	51.0 MPa	7400 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	25 %	25 %	Type I, 50 mm/min; ASTM D638
Flexural Yield Strength	75.0 MPa	10900 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.41 GPa	350 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	3.20 J/cm	5.99 ft-lb/in	ASTM D256
	1.86 J/cm @Temperature -40.0 Â°C	3.48 ft-lb/in @Temperature -40.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	110 Â°C @Thickness 6.40 mm	230 Â°F @Thickness 0.252 in	unannealed; ASTM D648
UL RTI, Electrical	50.0 Â°C	122 Â°F	UL 746B
UL RTI, Mechanical with Impact	50.0 Â°C	122 Â°F	UL 746B
UL RTI, Mechanical without Impact	50.0 Â°C	122 Â°F	UL 746B
Flammability, UL94	HB @Thickness 1.47 mm	HB @Thickness 0.0579 in	UL 94

Electrical Properties	Metric	English	Comments
Arc Resistance	0.00 - 60 sec	0.00 - 60 sec	Tungsten; ASTM D495

Electrical Properties	175 - 250 V Metric	175 - 250 V English	UL 746A Comments
Hot Wire Ignition, HWI	15 - 30 sec	15 - 30 sec	UL 746A
High Amp Arc Ignition, HAI	15 - 30 arcs	15 - 30 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	80.0 - 150 mm/min	3.15 - 5.91 in/min	UL 746A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China