

SABIC Innovative Plastics NORYL STN15 PPE+HIPS (Asia Pacific)

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polystyrene (PS)

Material Notes:

PPE+HIPS Unfilled Auto Interior

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-STN15-PPEHIPS-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.06 g/cc	1.06 g/cc	ASTM D792
Water Absorption	0.060 % @Time 86400 sec	0.060 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	6.4 g/10 min @Load 10.0 kg, Temperature 250 Â°C	6.4 g/10 min @Load 22.0 lb, Temperature 482 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	43.0 MPa	6240 psi	SABIC - Japan Method
Elongation at Break	80 %	80 %	SABIC - Japan Method
Flexural Strength	66.0 MPa	9570 psi	ASTM D790
Flexural Modulus	2.05 GPa	297 ksi	ASTM D790
Izod Impact, Notched	2.94 J/cm	5.51 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	80.0 Âµm/m-Â°C @Temperature -30.0 - 30.0 Â°C	44.4 Âµin/in-Â°F @Temperature -22.0 - 86.0 Â°F	TMA
Deflection Temperature at 1.8 MPa (264 psi)	117 Â°C @Thickness 6.40 mm	243 Â°F @Thickness 0.252 in	unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China