

SABIC Innovative Plastics PC1000 PC (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

PC1000R resin is a medium-low flow (MFR = 10 at 300°C/1.2kg), heat stabilized, polycarbonate product with mold release designed for use in the general purpose molding market.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-PC1000-PC-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.35 %	0.35 %	ASTM D570
Water Absorption at Saturation	0.35 %	0.35 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	on Tensile Bar; SABIC Method
	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	10 g/10 min @Load 1.20 kg, Temperature 300 °C	10 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238
Melt Index of Compound	9.0 g/10 min @Load 1.20 kg, Temperature 300 °C	9.0 g/10 min @Load 2.65 lb, Temperature 572 °F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
	120	120	ISO 2039-2
Tensile Strength, Yield	63.0 MPa	9140 psi	Type I, 50 mm/min; ASTM D638
	63.0 MPa	9140 psi	50 mm/min; ISO 527
Elongation at Break	>= 70 %	>= 70 %	Type I, 50 mm/min; ASTM D638
	>= 70 %	>= 70 %	50 mm/min; ISO 527
Elongation at Yield	6.0 %	6.0 %	Type I, 50 mm/min; ASTM D638
	6.0 %	6.0 %	50 mm/min; ISO 527

Tensile Modulus Mechanical Properties	2.35 GPa Metric	341 ksi English	50 mm/min; ASTM D638 Comments
	2.35 GPa	341 ksi	1 mm/min; ISO 527
Flexural Yield Strength	90.0 MPa	13100 psi	1.3 mm/min, 50 mm span; ASTM D790
	90.0 MPa	13100 psi	2 mm/min; ISO 178
Flexural Modulus	2.30 GPa	334 ksi	1.3 mm/min, 50 mm span; ASTM D790
	2.30 GPa	334 ksi	2 mm/min; ISO 178
Izod Impact, Notched	8.00 J/cm	15.0 ft-lb/in	ASTM D256
Izod Impact, Unnotched	NB	NB	ASTM D4812
Izod Impact, Notched (ISO)	70.0 kJ/m ²	33.3 ft-lb/in ²	80*10*3; ISO 180/1A
	12.0 kJ/m ² @Temperature -30.0 Â°C	5.71 ft-lb/in ² @Temperature -22.0 Â°F	80*10*3; ISO 180/1A
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	NB @Temperature -30.0 Â°C	NB @Temperature -22.0 Â°F	80*10*3; ISO 180/1U
Dart Drop, Total Energy	65.0 J	47.9 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 Âµm/m-Â°C @Temperature -40.0 - 95.0 Â°C	38.9 Âµin/in-Â°F @Temperature -40.0 - 203 Â°F	ASTM E 831
	70.0 Âµm/m-Â°C @Temperature 23.0 - 80.0 Â°C	38.9 Âµin/in-Â°F @Temperature 73.4 - 176 Â°F	ISO 11359-2
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ftÂ²- Â°F	ASTM C177
	0.200 W/m-K	1.39 BTU-in/hr-ftÂ²- Â°F	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	138 Â°C	280 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	138 Â°C @Thickness 3.20 mm	280 Â°F @Thickness 0.126 in	ASTM D648

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	127 Â°C	261 Â°F	ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	143 Â°C	289 Â°F	Rate B/50; ASTM D1525
	143 Â°C	289 Â°F	Rate B/50; ISO 306
Flammability, UL94	V-2	V-2	UL 94
	@Thickness 1.50 mm	@Thickness 0.0591 in	

Optical Properties	Metric	English	Comments
Refractive Index	1.586	1.586	ASTM D542
	1.586	1.586	ISO 489
Haze	<= 0.80 %	<= 0.80 %	ASTM D1003
	@Thickness 2.54 mm	@Thickness 0.100 in	
Transmission, Visible	88 - 90 %	88 - 90 %	2.54 mm; ASTM D1003

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	ASTM D257
	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Dielectric Constant	3.0	3.0	ASTM D150
	@Frequency 60.0 Hz	@Frequency 60.0 Hz	
	3.0	3.0	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	3.0	3.0	IEC 60250
	@Frequency 60.0 Hz	@Frequency 60.0 Hz	
	3.0	3.0	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	27.0 kV/mm	686 kV/in	ASTM D149
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	27.0 kV/mm	686 kV/in	IEC 60243-1
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Dissipation Factor			ASTM D150
	@Frequency 60.0 Hz	@Frequency 60.0 Hz	
	0.0010	0.0010	IEC 60250
	@Frequency 60.0 Hz	@Frequency 60.0 Hz	
	0.010	0.010	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	0.010	0.010	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	

Descriptive Properties	Value	Comments
Ball Pressure Test, 125Å°C +/- 2Å°C	Passes	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China