

SABIC Innovative Plastics ULTEM 1100 PEI (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

Material Notes:

Standard flow Polyetherimide (Tg 217C). UL94 V0, V2 and 5VA listing.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-ULTEM-1100-PEI-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in ³	ISO 1183
Moisture Absorption	0.650 %	0.650 %	23 ^o C / 50% RH; ISO 62
Water Absorption at Saturation	1.2 %	1.2 %	ISO 62
Linear Mold Shrinkage, Flow	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	on Tensile Bar; SABIC Method
Melt Index of Compound	12 g/10 min @Load 5.00 kg, Temperature 340 ^o C	12 g/10 min @Load 11.0 lb, Temperature 644 ^o F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	85.0 MPa	12300 psi	50 mm/min; ISO 527
Tensile Strength, Yield	110 MPa	16000 psi	50 mm/min; ISO 527
Elongation at Break	10 %	10 %	50 mm/min; ISO 527
Elongation at Yield	6.0 %	6.0 %	50 mm/min; ISO 527
Tensile Modulus	3.50 GPa	508 ksi	1 mm/min; ISO 527
Flexural Yield Strength	140 MPa	20300 psi	2 mm/min; ISO 178
Flexural Modulus	3.30 GPa	479 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	4.00 kJ/m ²	1.90 ft-lb/in ²	80*10*4; ISO 180/1A
	4.00 kJ/m ² @Temperature -30.0 ^o C	1.90 ft-lb/in ² @Temperature -22.0 ^o F	80*10*4; ISO 180/1A
Taber Abrasion, mg/1000 Cycles	10	10	CS-17, 1 kg; SABIC Method

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	50.0 ^o µm/m- ^o C @Temperature 23.0 -	27.8 ^o µin/in- ^o F @Temperature 73.4 -	ISO 11359-2

Thermal Properties	150 Â°C Metric	302 Â°F English	Comments
CTE, linear, Transverse to Flow	50.0 Âµm/m-Â°C @Temperature 23.0 - 150 Â°C	27.8 Âµin/in-Â°F @Temperature 73.4 - 302 Â°F	ISO 11359-2
Thermal Conductivity	0.260 W/m-K	1.80 BTU-in/hr-ftÂ²-Â°F	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	200 Â°C	392 Â°F	Edgew 120*10*4 sp=100mm; ISO 75/Be
Deflection Temperature at 1.8 MPa (264 psi)	185 Â°C	365 Â°F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
Vicat Softening Point	200 Â°C	392 Â°F	Rate B/50; ISO 306
	205 Â°C	401 Â°F	Rate B/120; ISO 306
	210 Â°C	410 Â°F	Rate A/50; ISO 306
Glass Transition Temp, Tg	217 Â°C	423 Â°F	
UL RTI, Electrical	170 Â°C	338 Â°F	UL 746B
UL RTI, Mechanical with Impact	170 Â°C	338 Â°F	UL 746B
UL RTI, Mechanical without Impact	170 Â°C	338 Â°F	UL 746B
Flammability, UL94	V-2 @Thickness 0.400 mm	V-2 @Thickness 0.0157 in	UL 94
	V-0 @Thickness 0.750 mm	V-0 @Thickness 0.0295 in	UL 94
	5VA @Thickness 3.00 mm	5VA @Thickness 0.118 in	UL 94
Oxygen Index	47 %	47 %	ISO 4589
Glow Wire Test	960 Â°C @Thickness 3.20 mm	1760 Â°F @Thickness 0.126 in	IEC 60695-2-12

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	ROA; IEC 60093
Dielectric Constant	3.5 @Frequency 50.0 - 60.0 Hz	3.5 @Frequency 50.0 - 60.0 Hz	IEC 60250

Electrical Properties Dielectric Strength	17.2 kV/mm Metric	437 kV/in English	Comments in oil, IEC 60243-1
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dissipation Factor	0.0016 @Frequency 50.0 - 60.0 Hz	0.0016 @Frequency 50.0 - 60.0 Hz	IEC 60250
Comparative Tracking Index	>= 100 V	>= 100 V	IEC 60112
	175 V	175 V	IEC 60112

Descriptive Properties	Value	Comments
Ball Pressure Test, 125Â°C +/- 2Â°C	PASSES	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China