

SABIC Innovative Plastics ULTEM 2110EPR PEI (Asia Pacific)

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

Material Notes:

10% Glass fiber filled, high flow Polyetherimide (Tg 217C) with internal mold release and enhanced electroplatability. ECO Conforming, UL94 V0 and 5VA listing.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-ULTEM-2110EPR-PEI-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.35 g/cc	1.35 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0070 - 0.0090 cm/cm @Thickness 3.20 mm	0.0070 - 0.0090 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0060 - 0.0080 cm/cm @Thickness 3.20 mm	0.0060 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	19 g/10 min @Load 6.60 kg, Temperature 337 Â°C	19 g/10 min @Load 14.6 lb, Temperature 639 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	119 MPa	17300 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	119 MPa	17300 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	3.0 %	3.0 %	Type I, 5 mm/min; ASTM D638
Elongation at Yield	3.0 %	3.0 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	5.24 GPa	760 ksi	5 mm/min; ASTM D638
Flexural Strength	193 MPa	28000 psi	2.6 mm/min, 100 mm span; ASTM D790
Flexural Yield Strength	199 MPa	28900 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	4.80 GPa	696 ksi	1.3 mm/min, 50 mm span; ASTM D790
	5.17 GPa	750 ksi	2.6 mm/min, 100 mm span; ASTM D790
Izod Impact, Notched	0.690 J/cm	1.29 ft-lb/in	ASTM D256
	3.50 J/cm @Thickness 3.20 mm	6.56 ft-lb/in @Thickness 0.126 in	ASTM D256

Mechanical Properties	Metric	English	Comments
Dart Drop, Total Energy	10.0 J @Temperature 23.0 Å°C	7.38 ft-lb @Temperature 73.4 Å°F	ASTM D3763

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	36.0 Åµm/m-Å°C @Temperature -40.0 - 40.0 Å°C	20.0 Åµin/in-Å°F @Temperature -40.0 - 104 Å°F	ASTM E 831
CTE, linear, Transverse to Flow	81.0 Åµm/m-Å°C @Temperature -40.0 - 40.0 Å°C	45.0 Åµin/in-Å°F @Temperature -40.0 - 104 Å°F	ASTM E 831
Deflection Temperature at 0.46 MPa (66 psi)	210 Å°C @Thickness 3.20 mm	410 Å°F @Thickness 0.126 in	unannealed; ASTM D648
	212 Å°C @Thickness 6.40 mm	414 Å°F @Thickness 0.252 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	205 Å°C @Thickness 3.20 mm	401 Å°F @Thickness 0.126 in	unannealed; ASTM D648
	207 Å°C @Thickness 6.40 mm	405 Å°F @Thickness 0.252 in	unannealed; ASTM D648
Vicat Softening Point	210 Å°C	410 Å°F	Rate B/50; ASTM D1525
Glass Transition Temp, Tg	217 Å°C	423 Å°F	
UL RTI, Electrical	105 Å°C	221 Å°F	UL 746B
UL RTI, Mechanical with Impact	105 Å°C	221 Å°F	UL 746B
UL RTI, Mechanical without Impact	105 Å°C	221 Å°F	UL 746B
Flammability, UL94	V-0 @Thickness 0.400 mm	V-0 @Thickness 0.0157 in	UL 94

Electrical Properties	Metric	English	Comments
Arc Resistance	60 - 120 sec	60 - 120 sec	Tungsten; ASTM D495
Comparative Tracking Index	100 - 175 V	100 - 175 V	UL 746A
Hot Wire Ignition, HWI	60 - 120 sec	60 - 120 sec	UL 746A

High Amp Arc Ignition, HAI Electrical Properties	15 - 30 arcs Metric	15 - 30 arcs English	UL 746A Comments
High Voltage Arc-Tracking Rate, HVTR	80.0 - 150 mm/min	3.15 - 5.91 in/min	UL 746A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China