

SABIC Innovative Plastics ULTEM AUT230 PEI

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

Material Notes:

Transparent polyetherimide (Tg 247 degC). Very low outgassing and plateout, for automotive lighting applications where highly metallized, reflective surfaces are required. Haze onset temperature of 230 degC (SABIC Innovative Plastics method)

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-ULTEM-AUT230-PEI.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 g/cc	1.30 g/cc	ASTM D792
Density	1.30 g/cc	0.0470 lb/in ³	ISO 1183
Moisture Absorption	0.600 %	0.600 %	23Â°C / 50% RH; ISO 62
Water Absorption at Saturation	1.75 %	1.75 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	on Tensile Bar; SABIC Method
	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Index of Compound	8.0 g/10 min @Load 5.00 kg, Temperature 360 Â°C	8.0 g/10 min @Load 11.0 lb, Temperature 680 Â°F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	78.0 MPa	11300 psi	5 mm/min; ISO 527
	96.0 MPa	13900 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	95.0 MPa	13800 psi	5 mm/min; ISO 527
	96.0 MPa	13900 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	16.8 %	16.8 %	5 mm/min; ISO 527
	25 %	25 %	Type I, 5 mm/min; ASTM D638
Elongation at Yield	6.0 %	6.0 %	Type I, 5 mm/min; ASTM D638
	8.5 %	8.5 %	5 mm/min; ISO 527
Tensile Modulus	3.11 GPa	451 ksi	1 mm/min; ISO 527

Mechanical Properties	Metric	English	Comments
	3.37 GPa	500 ksi	2 mm/min, ASTM D638
Flexural Yield Strength	123 MPa	17800 psi	2 mm/min; ISO 178
Flexural Modulus	3.08 GPa	447 ksi	2 mm/min; ISO 178
	3.17 GPa	460 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	0.690 J/cm	1.29 ft-lb/in	ASTM D256
	0.740 J/cm	1.39 ft-lb/in	ASTM D256
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Izod Impact, Unnotched	NB	NB	ASTM D4812
Izod Impact, Notched (ISO)	4.00 kJ/mÂ²	1.90 ft-lb/inÂ²	80*10*4; ISO 180/1A
	5.00 kJ/mÂ²	2.38 ft-lb/inÂ²	80*10*4; ISO 180/1A
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*4; ISO 180/1U
	NB	NB	80*10*4; ISO 180/1U
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Dart Drop, Total Energy	33.0 J	24.3 ft-lb	ASTM D3763
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	50.0 Âµm/m-Â°C	27.8 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 150 Â°C	@Temperature -40.0 - 302 Â°F	
	50.0 Âµm/m-Â°C	27.8 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 150 Â°C	@Temperature 73.4 - 302 Â°F	
CTE, linear, Transverse to Flow	50.0 Âµm/m-Â°C	27.8 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 150 Â°C	@Temperature -40.0 - 302 Â°F	
	50.0 Âµm/m-Â°C	27.8 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 150 Â°C	@Temperature 73.4 - 302 Â°F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (50 psi)	237 Â°C	459 Â°F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Deflection Temperature at 1.8 MPa (264 psi)	228 Â°C	442 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	217 Â°C	423 Â°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
	230 Â°C	446 Â°F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Vicat Softening Point	238 Â°C	460 Â°F	Rate B/120; ISO 306
	242 Â°C	468 Â°F	Rate B/50; ASTM D1525
	242 Â°C	468 Â°F	Rate B/50; ISO 306
Glass Transition Temp, Tg	247 Â°C	477 Â°F	

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

Descriptive Properties	Value	Comments
Ball Pressure Test, 125Â°C +/- 2Â°C	Passes	IEC 60695-10-2
Metallized Haze Onset	230Â°C	SABIC Method

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China