

SABIC Innovative Plastics ULTEM LTX300A PEI Copolymer

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

Material Notes:

High flow Polyetherimide blend with low toxicity, smoke and flame evolution. ECO Compliant, UL94 V0 listing in recognized colors.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-ULTEM-LTX300A-PEI-Copolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 g/cc	1.30 g/cc	ASTM D792
Density	1.30 g/cc	0.0470 lb/in ³	ISO 1183
Moisture Absorption	0.700 %	0.700 %	23Â°C / 50% RH; ISO 62
Water Absorption at Saturation	1.25 %	1.25 %	ISO 62
Linear Mold Shrinkage, Flow	0.0060 - 0.0080 cm/cm	0.0060 - 0.0080 in/in	on Tensile Bar; SABIC Method
	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	
Melt Flow	2.4 g/10 min	2.4 g/10 min	ASTM D1238
	@Load 6.60 kg, Temperature 295 Â°C	@Load 14.6 lb, Temperature 563 Â°F	
Melt Index of Compound	15 g/10 min	15 g/10 min	MVR [cm ³ /10 min]; ISO 1133
	@Load 5.00 kg, Temperature 340 Â°C	@Load 11.0 lb, Temperature 644 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, H358/30	127 MPa	18400 psi	ISO 2039-1
Tensile Strength at Break	75.0 MPa	10900 psi	5 mm/min; ISO 527
	85.0 MPa	12300 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	90.0 MPa	13100 psi	5 mm/min; ISO 527
	97.0 MPa	14100 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	25 %	25 %	5 mm/min; ISO 527
	30 %	30 %	Type I, 5 mm/min; ASTM D638

Elongation at Yield Mechanical Properties	6.0 % Metric	6.0 % English	5 mm/min; ISO 527 Comments
	7.0 %	7.0 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	3.20 GPa	464 ksi	1 mm/min; ISO 527
	3.31 GPa	480 ksi	5 mm/min; ASTM D638
Flexural Yield Strength	130 MPa	18900 psi	2 mm/min; ISO 178
	145 MPa	21000 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	3.20 GPa	464 ksi	2 mm/min; ISO 178
	3.24 GPa	470 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	0.690 J/cm	1.29 ft-lb/in	ASTM D256
	20.8 J/cm	39.0 ft-lb/in	ASTM D256
	@Thickness 3.20 mm	@Thickness 0.126 in	
Izod Impact, Unnotched	21.0 J/cm	39.3 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	7.00 kJ/mÂ²	3.33 ft-lb/inÂ²	80*10*4; ISO 180/1A
	5.00 kJ/mÂ²	2.38 ft-lb/inÂ²	80*10*4; ISO 180/1A
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*4; ISO 180/1U
	NB	NB	80*10*4; ISO 180/1U
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*4 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*4 sp=62mm; ISO 179/1eU
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Charpy Impact, Notched	0.700 J/cmÂ²	3.33 ft-lb/inÂ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
	0.600 J/cmÂ²	2.86 ft-lb/inÂ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Gardner Impact	35.0 J	25.8 ft-lb	ASTM D3029
	40.0 J	29.5 ft-lb	

Dart Drop, Total Energy Mechanical Properties	Metric @Temperature 23.0 Â°C	English @Temperature 73.4 Â°F	ASTM D3763 Comments
Taber Abrasion, mg/1000 Cycles	15	15	CS-17, 1 kg; SABIC Method

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	50.0 Âµm/m-Â°C	27.8 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 150 Â°C	@Temperature -40.0 - 302 Â°F	
	50.0 Âµm/m-Â°C	27.8 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 150 Â°C	@Temperature 73.4 - 302 Â°F	
CTE, linear, Transverse to Flow	50.0 Âµm/m-Â°C	27.8 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 150 Â°C	@Temperature -40.0 - 302 Â°F	
	50.0 Âµm/m-Â°C	27.8 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 150 Â°C	@Temperature 73.4 - 302 Â°F	
Thermal Conductivity	0.260 W/m-K	1.80 BTU-in/hr-ftÂ²- Â°F	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	200 Â°C	392 Â°F	Edgew 120*10*4 sp=100mm; ISO 75/Be
	201 Â°C	394 Â°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
	204 Â°C	399 Â°F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Deflection Temperature at 1.8 MPa (264 psi)	185 Â°C	365 Â°F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
	187 Â°C	369 Â°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
	189 Â°C	372 Â°F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Vicat Softening Point	200 Â°C	392 Â°F	Rate B/50; ISO 306
	200 Â°C	392 Â°F	Rate B/120; ISO 306
	210 Â°C	410 Â°F	Rate B/50; ASTM D1525
	210 Â°C	410 Â°F	Rate A/50; ISO 306

Thermal Properties	V-0 Metric	V-0 English	Comments
Flammability, UL 94	@Thickness 0.750 mm	@Thickness 0.0295 in	UL 94 V0 SABIC-IP

Descriptive Properties	Value	Comments
Ball Pressure Test, 125Â°C +/- 2Â°C	Passes	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China