

SABIC Innovative Plastics Ultem 1010A PEI (Asia Pacific)

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

Material Notes:

Transparent, high flow Polyetherimide (Tg 217C). ECO Conforming. This data was supplied by SABIC-IP for the Asia Pacific region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Ultem-1010A-PEI-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.27 g/cc	1.27 g/cc	ASTM D 792
Density	1.27 g/cc	0.0459 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.70 %	0.70 %	23 ^o C / 50% RH; ISO 62
Water Absorption at Saturation	1.25 % @Temperature 23.0 ^o C	1.25 % @Temperature 73.4 ^o F	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	17.8 g/10 min @Load 6.60 kg, Temperature 337 ^o C	17.8 g/10 min @Load 14.6 lb, Temperature 639 ^o F	ASTM D 1238
	25 g/10 min @Load 5.00 kg, Temperature 360 ^o C	25 g/10 min @Load 11.0 lb, Temperature 680 ^o F	[cm ³ /10 min] Melt Volume Rate; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	85.0 MPa	12300 psi	5 mm/min; ISO 527
	105 MPa	15200 psi	Type I, 5 mm/min; ASTM D 638
Tensile Strength, Yield	105 MPa	15200 psi	5 mm/min; ISO 527
	110 MPa	16000 psi	Type I, 5 mm/min; ASTM D 638
Elongation at Break	60 %	60 %	Type I, 5 mm/min; ASTM D 638
	60 %	60 %	5 mm/min; ISO 527
Elongation at Yield	6.0 %	6.0 %	5 mm/min; ISO 527
	7.0 %	7.0 %	Type I, 5 mm/min; ASTM D 638
Tensile Modulus	3.20 GPa	464 ksi	1 mm/min; ISO 527

Mechanical Properties	Metric	English	Comments
Flexural Yield Strength	160 MPa	23200 psi	2 mm/min; ISO 178
	165 MPa	23900 psi	1.3 mm/min, 50 mm span; ASTM D 790
Flexural Modulus	3.30 GPa	479 ksi	2 mm/min; ISO 178
	3.52 GPa	511 ksi	1.3 mm/min, 50 mm span; ASTM D 790
Izod Impact, Notched	0.320 J/cm @Temperature 23.0 °C	0.599 ft-lb/in @Temperature 73.4 °F	ASTM D 256
	0.350 J/cm @Temperature -30.0 °C	0.656 ft-lb/in @Temperature -22.0 °F	ASTM D 256
Izod Impact, Unnotched	13.35 J/cm @Temperature 23.0 °C	25.01 ft-lb/in @Temperature 73.4 °F	ASTM D 4812
Izod Impact, Notched (ISO)	5.00 kJ/m ² @Temperature 23.0 °C	2.38 ft-lb/in ² @Temperature 73.4 °F	80*10*4; ISO 180/1A
	5.00 kJ/m ² @Temperature -30.0 °C	2.38 ft-lb/in ² @Temperature -22.0 °F	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	80*10*4; ISO 180/1U
	NB @Temperature -30.0 °C	NB @Temperature -22.0 °F	80*10*4; ISO 180/1U
Charpy Impact, Notched	0.300 J/cm ² @Temperature 23.0 °C	1.43 ft-lb/in ² @Temperature 73.4 °F	V-notch Edgew 80*10*4 sp=62mm; ISO 179/1eA
Impact Test	33.0 J @Temperature 23.0 °C	24.3 ft-lb @Temperature 73.4 °F	Instrumented Impact Total Energy; ASTM D 3763

Thermal Properties	Metric	English	Comments
	50.0 Åµm/m-Å°C	27.8 Åµin/in-Å°F	

CTE, linear, Parallel to Flow Thermal Properties	Metric @ Temperature 23.0 - 150 Â°C	English @ Temperature 73.4 - 302 Â°F	ISO 11359-2 Comments
	55.0 Âµm/m-Â°C	30.6 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 150 Â°C	@Temperature -40.0 - 302 Â°F	
CTE, linear, Transverse to Flow	50.0 Âµm/m-Â°C	27.8 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 150 Â°C	@Temperature 73.4 - 302 Â°F	
	55.0 Âµm/m-Â°C	30.6 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 150 Â°C	@Temperature -40.0 - 302 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	205 Â°C	401 Â°F	unannealed; ASTM D 648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	190 Â°C	374 Â°F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
	193 Â°C	379 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	197 Â°C	387 Â°F	unannealed; ASTM D 648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	211 Â°C	412 Â°F	Rate B/50; ISO 306
	212 Â°C	414 Â°F	Rate B/120; ISO 306
	219 Â°C	426 Â°F	Rate B/50; ASTM D 1525
Glass Transition Temp, Tg	217 Â°C	423 Â°F	

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China