

SABIC Innovative Plastics Ultem XH6050F PEI Copolymer (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

Material Notes:

Transparent, enhanced flow Polyetherimidesulfone copolymer (Tg 247C). ECO Conforming. US FDA Compliant. Resin is subject to U.S. Commerce Control Laws (15CFR Chapter VII, Part 774). This data was supplied by SABIC-IP for the Europe-Africa-Middle East region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Ultem-XH6050F-PEI-Copolymer-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 g/cc	1.30 g/cc	ASTM D 792
Density	1.30 g/cc	0.0470 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.60 %	0.60 %	23Â°C / 50% RH; ISO 62
Water Absorption at Saturation	1.75 % @Temperature 23.0 Â°C	1.75 % @Temperature 73.4 Â°F	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	on tensile bar; SABIC Method
	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	8.0 g/10 min @Load 5.00 kg, Temperature 360 Â°C	8.0 g/10 min @Load 11.0 lb, Temperature 680 Â°F	[cm ³ /10 min] Melt Volume Rate; ISO 1133
	12.5 g/10 min @Load 6.60 kg, Temperature 367 Â°C	12.5 g/10 min @Load 14.6 lb, Temperature 693 Â°F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Hardness, H358/30	140 MPa	20300 psi	ISO 2039-1
Tensile Strength at Break	78.0 MPa	11300 psi	5 mm/min; ISO 527
	96.0 MPa	13900 psi	Type I, 5 mm/min; ASTM D 638
Tensile Strength, Yield	95.0 MPa	13800 psi	5 mm/min; ISO 527
	96.0 MPa	13900 psi	Type I, 5 mm/min; ASTM D 638

Mechanical Properties	Metric	English	Comments
Elongation at Break	16.9 %	16.9 %	5 mm/min; ISO 527
	25 %	25 %	Type I, 5 mm/min; ASTM D 638
Elongation at Yield	6.0 %	6.0 %	Type I, 5 mm/min; ASTM D 638
	8.5 %	8.5 %	5 mm/min; ISO 527
Tensile Modulus	3.11 GPa	451 ksi	1 mm/min; ISO 527
	3.51 GPa	509 ksi	5 mm/min; ASTM D 638
Flexural Strength	159 MPa	23100 psi	1.3 mm/min, 50 mm span; ASTM D 790
Flexural Yield Strength	123 MPa	17800 psi	2 mm/min; ISO 178
	155 MPa	22500 psi	2.6 mm/min, 100 mm span; ASTM D 790
Flexural Modulus	3.08 GPa	447 ksi	2 mm/min; ISO 178
	3.10 GPa	450 ksi	2.6 mm/min, 100 mm span; ASTM D 790
	3.17 GPa	460 ksi	1.3 mm/min, 50 mm span; ASTM D 790
Izod Impact, Notched	0.690 J/cm @Temperature 23.0 Â°C	1.29 ft-lb/in @Temperature 73.4 Â°F	ASTM D 256
	0.740 J/cm @Temperature -30.0 Â°C	1.39 ft-lb/in @Temperature -22.0 Â°F	ASTM D 256
Izod Impact, Unnotched	NB @Temperature 23.0 Â°C	NB @Temperature 73.4 Â°F	ASTM D 4812
Izod Impact, Notched (ISO)	4.00 kJ/mÂ² @Temperature 23.0 Â°C	1.90 ft-lb/inÂ² @Temperature 73.4 Â°F	80*10*4; ISO 180/1A
	5.00 kJ/mÂ² @Temperature -30.0 Â°C	2.38 ft-lb/inÂ² @Temperature -22.0 Â°F	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	NB @Temperature 23.0 Â°C	NB @Temperature 73.4 Â°F	80*10*4; ISO 180/1U
	NB	NB	80*10*4; ISO 180/1U

Mechanical Properties	Metric @Temperature -30.0 Â°C	English @Temperature -22.0 Â°F	Comments
Charpy Impact Unnotched	NB @Temperature 23.0 Â°C	NB @Temperature 73.4 Â°F	Edgew 80*10*4 sp=62mm; ISO 179/1eU
	NB @Temperature -30.0 Â°C	NB @Temperature -22.0 Â°F	Edgew 80*10*4 sp=62mm; ISO 179/1eU
Impact Test	33.0 J @Temperature 23.0 Â°C	24.3 ft-lb @Temperature 73.4 Â°F	Instrumented Impact Total Energy; ASTM D 3763

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	50.0 Âµm/m-Â°C @Temperature -40.0 - 150 Â°C	27.8 Âµin/in-Â°F @Temperature -40.0 - 302 Â°F	ASTM E 831
	50.0 Âµm/m-Â°C @Temperature 23.0 - 150 Â°C	27.8 Âµin/in-Â°F @Temperature 73.4 - 302 Â°F	ISO 11359-2
CTE, linear, Transverse to Flow	50.0 Âµm/m-Â°C @Temperature -40.0 - 150 Â°C	27.8 Âµin/in-Â°F @Temperature -40.0 - 302 Â°F	ASTM E 831
	50.0 Âµm/m-Â°C @Temperature 23.0 - 150 Â°C	27.8 Âµin/in-Â°F @Temperature 73.4 - 302 Â°F	ISO 11359-2
Thermal Conductivity	0.220 W/m-K	1.53 BTU-in/hr-ftÂ²- Â°F	ASTM E 1530
Deflection Temperature at 0.46 MPa (66 psi)	222 Â°C @Thickness 3.20 mm	432 Â°F @Thickness 0.126 in	unannealed; ASTM D 648
	237 Â°C @Thickness 6.40 mm	459 Â°F @Thickness 0.252 in	unannealed; ASTM D 648
Deflection Temperature at 1.8 MPa (264 psi)	228 Â°C	442 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	217 Â°C @Thickness 3.20 mm	423 Â°F @Thickness 0.126 in	unannealed; ASTM D 648
	230 Â°C @Thickness 6.40 mm	446 Â°F @Thickness 0.252 in	unannealed; ASTM D 648

Thermal Properties	Metric	English	Comments
Vicat Softening Point	242 Â°C	468 Â°F	Rate B/50; ASTM D 1525
	242 Â°C	468 Â°F	Rate B/50; ISO 306
	247 Â°C	477 Â°F	
Glass Transition Temp, Tg	247 Â°C	477 Â°F	
Oxygen Index	45 %	45 %	LOI; ISO 4589
Glow Wire Test	850 Â°C	1560 Â°F	Glow Wire Ignitability Temperature; IEC 60695-2-13
	@Thickness 3.00 mm	@Thickness 0.118 in	
	960 Â°C	1760 Â°F	Glow Wire Flammability Index; IEC 60695-2-12
	@Thickness 3.20 mm	@Thickness 0.126 in	

Optical Properties	Metric	English	Comments
Haze	2.0 %	2.0 %	ASTM D 1003
	@Thickness 2.54 mm	@Thickness 0.100 in	
Transmission, Visible	58 %	58 %	ASTM D 1003
	@Thickness 2.54 mm	@Thickness 0.100 in	

Electrical Properties	Metric	English	Comments
Dielectric Strength	17.0 kV/mm	432 kV/in	in oil; ASTM D 149
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dissipation Factor	0.0010	0.0010	IEC 60250
	@Frequency 1000 Hz	@Frequency 1000 Hz	
	0.0070	0.0070	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	0.0080	0.0080	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.025	0.025	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Comparative Tracking Index	175 V	175 V	IEC 60112

Descriptive Properties	Value	Comments
Ball Pressure Test, 125Â°C +/- 2Â°C	Passes	IEC 60695-10-2

Descriptive Properties	Value	Comments
------------------------	-------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China