

SABIC Innovative Plastics Xenoy® 5720U PBT+PC (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/Polybutylene Terephthalate (PBT) Blend, Unreinforced , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

Unfilled PBT+PC alloy. Outstanding low temperature impact/chemical resistance. UV stabilized version of XENOV

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Xenoy-5720U-PBTPC-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in ³	ASTM D792
	1.17 g/cc	0.0423 lb/in ³	ISO 1183
Moisture Absorption	0.0800 %	0.0800 %	23Â°C / 50% RH; ISO 62
Water Absorption at Saturation	0.28 %	0.28 %	ISO 62
Linear Mold Shrinkage, Flow	0.010 - 0.012 cm/cm	0.010 - 0.012 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	
Melt Flow	3.0 g/10 min	3.0 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 250 Â°C	@Load 4.76 lb, Temperature 482 Â°F	
	3.8 g/10 min	3.8 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 250 Â°C	@Load 4.76 lb, Temperature 482 Â°F	
	6.0 g/10 min	6.0 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 265 Â°C	@Load 4.76 lb, Temperature 509 Â°F	
	11 g/10 min	11 g/10 min	ISO 1133
	@Load 5.00 kg, Temperature 250 Â°C	@Load 11.0 lb, Temperature 482 Â°F	
	11.4 g/10 min	11.4 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 250 Â°C	@Load 11.0 lb, Temperature 482 Â°F	
	19.7 g/10 min	19.7 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 266 Â°C	@Load 11.0 lb, Temperature 511 Â°F	
Melt Index of Compound	3.0 g/10 min	3.0 g/10 min	MVR [cm ³ /10 min]; ISO 1133
	@Load 2.16 kg,	@Load 4.76 lb,	

Physical Properties	Temperature 250 Â°C Metric	Temperature 482 Â°F English	Comments
	6.0 g/10 min	6.0 g/10 min	
	@Load 2.16 kg, Temperature 265 Â°C	@Load 4.76 lb, Temperature 509 Â°F	MVR [cm^3/10 min]; ISO 1133
	10 g/10 min	10 g/10 min	
	@Load 5.00 kg, Temperature 250 Â°C	@Load 11.0 lb, Temperature 482 Â°F	MVR [cm^3/10 min]; ISO 1133
	18 g/10 min	18 g/10 min	
	@Load 5.00 kg, Temperature 265 Â°C	@Load 11.0 lb, Temperature 509 Â°F	MVR [cm^3/10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	43.0 MPa	6240 psi	5 mm/min; ISO 527
	43.0 MPa	6240 psi	50 mm/min; ISO 527
	47.0 MPa	6820 psi	Type I, 10 mm/min; SABIC - Japan Method
	48.0 MPa	6960 psi	Type I, 50 mm/min; ASTM D638
	50.0 MPa	7250 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	44.0 MPa	6380 psi	5 mm/min; ISO 527
	44.0 MPa	6380 psi	Type I, 5 mm/min; ASTM D638
	45.0 MPa	6530 psi	Type I, 10 mm/min; SABIC - Japan Method
	47.0 MPa	6820 psi	50 mm/min; ISO 527
	47.0 MPa	6820 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	106.8 %	106.8 %	5 mm/min; ISO 527
	109.5 %	109.5 %	Type I, 10 mm/min; SABIC - Japan Method
	115.3 %	115.3 %	50 mm/min; ISO 527
	116.6 %	116.6 %	Type I, 50 mm/min; ASTM D638
	122.4 %	122.4 %	Type I, 5 mm/min; ASTM D638
Elongation at Yield	4.0 %	4.0 %	Type I, 50 mm/min; ASTM D638
	4.1 %	4.1 %	5 mm/min; ISO 527
	4.6 %	4.6 %	50 mm/min; ISO 527

Mechanical Properties	4.6 % Metric	4.6 % English	Type I, 5 mm/min; ASTM D638 Comments
	4.6 %	4.6 %	Type I, 10 mm/min; SABIC - Japan Method
Tensile Modulus	1.79 GPa	260 ksi	1 mm/min; ISO 527
	1.81 GPa	263 ksi	50 mm/min; ASTM D638
	1.83 GPa	265 ksi	5 mm/min; ASTM D638
	1.83 GPa	265 ksi	10 mm/min; SABIC - Japan Method
Flexural Strength	69.0 MPa	10000 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Yield Strength	70.0 MPa	10200 psi	1.3 mm/min, 50 mm span; ASTM D790
	71.0 MPa	10300 psi	2 mm/min; ISO 178
Flexural Modulus	1.66 GPa	241 ksi	1.3 mm/min, 50 mm span; ASTM D790
	1.86 GPa	270 ksi	2 mm/min; ISO 178
Izod Impact, Notched	7.22 J/cm	13.5 ft-lb/in	ASTM D256
	5.98 J/cm	11.2 ft-lb/in	
	@Temperature -40.0 Â°C	@Temperature -40.0 Â°F	ASTM D256
	6.47 J/cm	12.1 ft-lb/in	
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	ASTM D256
	6.63 J/cm	12.4 ft-lb/in	
	@Temperature -10.0 Â°C	@Temperature 14.0 Â°F	ASTM D256
	6.91 J/cm	12.9 ft-lb/in	
	@Temperature 0.000 Â°C	@Temperature 32.0 Â°F	ASTM D256
	6.95 J/cm	13.0 ft-lb/in	
	@Temperature -20.0 Â°C	@Temperature -4.00 Â°F	ASTM D256
Izod Impact, Notched (ISO)	55.0 kJ/mÂ²	26.2 ft-lb/inÂ²	80*10*4; ISO 180/1A
	46.0 kJ/mÂ²	21.9 ft-lb/inÂ²	
	@Temperature -40.0 Â°C	@Temperature -40.0 Â°F	80*10*4; ISO 180/1A
	48.0 kJ/mÂ²	22.8 ft-lb/inÂ²	

Mechanical Properties	Metric @ Temperature -30.0 Â°C	English @ Temperature -22.0 Â°F	Comments 80*10*4; ISO 180/1A
	50.0 kJ/mÂ²	23.8 ft-lb/inÂ²	80*10*4; ISO 180/1A
	@Temperature -20.0 Â°C	@Temperature -4.00 Â°F	
	52.0 kJ/mÂ²	24.7 ft-lb/inÂ²	80*10*4; ISO 180/1A
	@Temperature -10.0 Â°C	@Temperature 14.0 Â°F	
	55.0 kJ/mÂ²	26.2 ft-lb/inÂ²	80*10*4; ISO 180/1A
	@Temperature 0.000 Â°C	@Temperature 32.0 Â°F	
Charpy Impact, Notched	5.50 J/cmÂ²	26.2 ft-lb/inÂ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
	4.70 J/cmÂ²	22.4 ft-lb/inÂ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Dart Drop, Total Energy	44.0 J	32.5 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763
	41.0 J	30.2 ft-lb	Instrumented Impact, Energy @ peak, -20Â°C; ASTM D3763
	@Temperature -20.0 Â°C	@Temperature -4.00 Â°F	
	49.0 J	36.1 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
	49.0 J	36.1 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763
	@Temperature -40.0 Â°C	@Temperature -40.0 Â°F	
	53.0 J	39.1 ft-lb	ASTM D3763
	@Temperature -20.0 Â°C	@Temperature -4.00 Â°F	
	54.0 J	39.8 ft-lb	ASTM D3763
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
	59.0 J	43.5 ft-lb	ASTM D3763
	@Temperature -40.0 Â°C	@Temperature -40.0 Â°F	
	61.0 J	45.0 ft-lb	ASTM D3763
	@Temperature -30.0	@Temperature -22.0	

Mechanical Properties	°C Metric	°F English	Comments
Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	97.5 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	54.2 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTME 831
	@Temperature -40.0 - 95.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 203 $\text{Å}^\circ\text{F}$	
	97.5 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	54.2 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ISO 11359-2
	@Temperature -30.0 - 80.0 $\text{Å}^\circ\text{C}$	@Temperature -22.0 - 176 $\text{Å}^\circ\text{F}$	
CTE, linear, Transverse to Flow	100 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	55.6 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTME 831
	@Temperature -40.0 - 95.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 203 $\text{Å}^\circ\text{F}$	
	100 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	55.6 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ISO 11359-2
	@Temperature -30.0 - 80.0 $\text{Å}^\circ\text{C}$	@Temperature -22.0 - 176 $\text{Å}^\circ\text{F}$	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China