

SABIC PP 5702P Polypropylene Homopolymer for Injection Molding

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

Product Description: PP 5702P is specially developed for rigid injection molded articles for general purpose applications. It gives consistent processability and high gloss in the products. **Typical Applications:** PP 5702P can be used mainly for housewares articles, food containers, garden furniture and toys. Information provided by SABIC.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-PP-5702P-Polypropylene-Homopolymer-for-Injection-Molding.php

Physical Properties	Metric	English	Comments
Density	0.905 g/cc	0.0327 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.012 - 0.025 cm/cm	0.012 - 0.025 in/in	
Melt Flow	9.0 g/10 min @Load 2.16 kg, Temperature 230 °C	9.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	102	102	ASTM D785
Tensile Strength, Yield	35.0 MPa	5080 psi	ASTM D638
Elongation at Yield	12 %	12 %	ASTM D638
Flexural Modulus, 1% Secant	1550 MPa	225000 psi	ASTM D790A
Izod Impact, Notched	0.370 J/cm	0.693 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	94.0 °C	201 °F	ASTM D648
Vicat Softening Point	154 °C	309 °F	ASTM D1525B

Processing Properties	Metric	English	Comments
Processing Temperature	220 - 240 °C	428 - 464 °F	Barrel Temperature
Mold Temperature	15.0 - 40.0 °C	59.0 - 104 °F	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China