

SCG Chemicals EL-Pro, P722JO Polypropylene Injection Molding

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

Key Characteristics: Good flowability, Good sealability, Good mechanical property balance, Minimal shrinkage and warpage, Contains UV stabilizer.
Recommended Applications: Good impact automotive and electrical appliance parts, Battery case that require excellent properties.
 Information provided by SCG Chemicals

Order this product through the following link:

http://www.lookpolymers.com/polymer_SCG-Chemicals-EL-Pro-P722JO-Polypropylene-Injection-Molding.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.910 g/cc	0.910 g/cc	ASTM D1505
Linear Mold Shrinkage, Flow	0.0152 cm/cm @Thickness 2.00 mm	0.0152 in/in @Thickness 0.0787 in	TPE Method
Linear Mold Shrinkage, Transverse	0.014 cm/cm @Thickness 2.00 mm	0.014 in/in @Thickness 0.0787 in	TPE Method
Melt Flow	10 g/10 min @Load 2.16 kg, Temperature 230 °C	10 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	75	75	ASTM D785
Tensile Strength at Break	18.0 MPa	2610 psi	ASTM D638
Tensile Strength, Yield	29.4 MPa	4270 psi	ASTM D638
Elongation at Break	200 %	200 %	ASTM D638
Flexural Modulus	1.27 GPa	185 ksi	ASTM D790
Izod Impact, Notched	0.490 J/cm @Temperature -20.0 °C	0.918 ft-lb/in @Temperature -4.00 °F	ASTM D256
	0.686 J/cm @Temperature 0.000 °C	1.29 ft-lb/in @Temperature 32.0 °F	ASTM D256
	0.981 J/cm @Temperature 23.0 °C	1.84 ft-lb/in @Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	163 Â°C	325 Â°F	ASTM D2117
Deflection Temperature at 0.46 MPa (66 psi)	110 Â°C	230 Â°F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	55.0 Â°C	131 Â°F	ASTM D648
Vicat Softening Point	150 Â°C	302 Â°F	ASTM D1525
Brittleness Temperature	-20.0 Â°C	-4.00 Â°F	ASTM D746

Optical Properties	Metric	English	Comments
Haze	80 % @Thickness 1.00 mm	80 % @Thickness 0.0394 in	ASTM D1003
Gloss	30 % @Thickness 1.00 mm	30 % @Thickness 0.0394 in	ASTM D2457

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China