

SGL Carbon Group EK 201 Graphite

Category : Carbon , Graphite

Material Notes:

Good mechanical strength, good sliding properties, high temperature resistance, high thermal shock resistance, low wettability, high corrosion resistance, high thermal conductivity, high purity, and good electrical conductivity. Typical Applications: Bearings, seals for compressors. Certified for use in potable water and/or in foodstuff. Information provided by SGL Carbon Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_SGL-Carbon-Group-EK-201-Graphite.php

Physical Properties	Metric	English	Comments
Density	1.82 g/cc	0.0658 lb/in ³	
Open Porosity	<= 2.5 %	<= 2.5 %	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	Size/Load - 10/150
Modulus of Elasticity	13.8 GPa	2000 ksi	
Flexural Strength	48.3 MPa	7000 psi	
Compressive Strength	221 MPa	32000 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	7.74 Åµm/m-Å°C @Temperature 20.0 Å°C	4.30 Åµin/in-Å°F @Temperature 68.0 Å°F	
Thermal Conductivity	25.9 W/m-K	180 BTU-in/hr-ftÅ²-Å°F	
Maximum Service Temperature, Air	260 Å°C	500 Å°F	In oxygen
Maximum Service Temperature, Inert	260 Å°C	500 Å°F	Reducing Atm.

Descriptive Properties	Value	Comments
Impregnation	Resin	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China