

SGL Carbon Group EK 2243 Carbon Graphite

Category : Carbon , Graphite

Material Notes:

Good mechanical strength, good sliding properties, high temperature resistance, high thermal shock resistance, low wettability, high corrosion resistance, high thermal conductivity, high purity, and good electrical conductivity. Typical Applications: Dry Running
Seals Certified for use in potable water and/or in foodstuff Information provided by SGL Carbon Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_SGL-Carbon-Group-EK-2243-Carbon-Graphite.php

Physical Properties	Metric	English	Comments
Density	1.79 g/cc	0.0647 lb/in ³	
Open Porosity	<= 2.5 %	<= 2.5 %	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	110	110	Size/Load - 5/100
Modulus of Elasticity	17.9 GPa	2600 ksi	
Flexural Strength	58.6 MPa	8500 psi	
Compressive Strength	200 MPa	29000 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	5.04 Åµm/m-Å°C @Temperature 20.0 Å°C	2.80 Åµin/in-Å°F @Temperature 68.0 Å°F	
Thermal Conductivity	17.3 W/m-K	120 BTU-in/hr-ftÅ²-Å°F	
Maximum Service Temperature, Air	177 Å°C	350 Å°F	In oxygen
Maximum Service Temperature, Inert	177 Å°C	351 Å°F	Reducing Atm.

Descriptive Properties	Value	Comments
Impregnation	Resin	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China