

SGL Carbon Group SIGRAFIL C® C30 T400 EPY Continuous Tow Carbon Fiber with 400k filaments, Epoxy Sizing

Category: Carbon, Carbon Fiber, Other Engineering Material, Composite Fibers

Material Notes:

SIGRAFIL C as continuous tow is ideal for waving, prepregging, filament winding, Carbon Fiber Reinforced Plastics (CFRP) components, advanced composites, multi-axial production, unidirectional tapes, extrusion, pultrusion and other conversion processing. Characteristic properties of SIGRAFIL C include high tensile strength, high modulus of elasticity coupled with high electrical conductivity and compatibility with a large variety of resins.Information provided by SGL Carbon Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_SGL-Carbon-Group-SIGRAFIL-C-C30-T400-EPY-Continuous-Tow-Carbon-Fiber-with-400k-filaments-Epoxy-Sizing.php

Physical Properties	Metric	English	Comments
Density	1.80 g/cc	0.0650 lb/in³	Fiber Density
Filament Diameter	7.0 µm	7.0 µm	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	3800 MPa	551000 psi	ASTM D3379-78
Elongation at Break	1.5 %	1.5 %	ASTM D3379-75
Modulus of Elasticity	240 GPa	34800 ksi	ASTM D3379-78

Electrical Properties	Metric	English	Comments
Volume Resistivity	0.0016 ohm-cm	0.0016 ohm-cm	

Descriptive Properties	Value	Comments
Carbon Content, wt %	>95	
Sizing Content, % by weight	1	
Weight per unit length, g/m	25	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers



Address: United North Road 215, Fengxian District, Shanghai City, China