

SK Chemicals SKYTHANE® S395A Polyester Based Thermoplastic Polyurethane Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Polyester Grade

Material Notes:

Description: SK Chemicals has supplied Thermoplastic Polyurethane Elastomer (TPU) under the name of SKYTHANE. Applications include: Keyboard Covers, Outsoles of Soccer Shoes, Wire and Cable, Airbags, Sheets and Film, Hoses and Tubing, Shoe Components, Fire Hoses. Information provided by SK Chemicals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SK-Chemicals-SKYTHANE-S395A-Polyester-Based-Thermoplastic-Polyurethane-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.23 g/cc	1.23 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	95	95	ASTM D2240
Hardness, Shore D	52	52	ASTM D2240
Tensile Strength, Ultimate	46.1 MPa	6680 psi	ASTM D412
Elongation at Break	530 %	530 %	ASTM D412
100% Modulus	0.0142 GPa	2.06 ksi	ASTM D412
300% Modulus	0.0296 GPa	4.30 ksi	ASTM D412
Resilience	35	35	Vertical Rebound; ASTM D2632
Tear Strength	157 kN/m	896 pli	Die C; ASTM D624
Taber Abrasion, mg/1000 Cycles	45	45	H18 wheel, 1000g load; ASTM D1044

Thermal Properties	Metric	English	Comments
Vicat Softening Point	115 Â°C	239 Â°F	ASTM D1525

Processing Properties	Metric	English	Comments
Processing Temperature	200 Â°C	392 Â°F	Transition Temperature
	200 Â°C	392 Â°F	Metering Temperature
Middle Barrel Temperature	195 Â°C	383 Â°F	

Nozzle Temperature Processing Properties	205 Â°C Metric	401 Â°F English	Comments
Zone 1	185 Â°C	365 Â°F	
Zone 2	190 Â°C	374 Â°F	
Zone 3	195 Â°C	383 Â°F	
Zone 4	200 Â°C	392 Â°F	
Adapter Temperature	200 Â°C	392 Â°F	
Die Temperature	200 Â°C	392 Â°F	Tip
	205 Â°C	401 Â°F	Body
Mold Temperature	20.0 - 40.0 Â°C	68.0 - 104 Â°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China