

SSAB Tunplat Docol® 800 DL High-strength Steel

Category : Metal , Ferrous Metal , Alloy Steel , Low Alloy Steel

Material Notes:

In course of development.Data provided by SSAB Tunplat.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SSAB-Tunplat-Docol-800-DL-High-strength-Steel.php

Physical Properties	Metric	English	Comments
Density	7.87 g/cc	0.284 lb/in ³	Estimated by MatWeb

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	800 - 950 MPa	116000 - 138000 psi	
Tensile Strength, Yield	>= 550 MPa	>= 79800 psi	After bake hardening
	390 - 540 MPa	56600 - 78300 psi	
	@Strain 0.200 %	@Strain 0.200 %	
Elongation at Break	>= 13 %	>= 13 %	A₈₀
Bend Radius, Minimum	>= 1.0 t	>= 1.0 t	90° bend

Component Elements Properties	Metric	English	Comments
Aluminum, Al	0.040 %	0.040 %	
Carbon, C	0.14 %	0.14 %	
Iron, Fe	98 %	98 %	As remainder
Manganese, Mn	1.7 %	1.7 %	
Niobium, Nb (Columbium, Cb)	0.015 %	0.015 %	
Phosphorous, P	0.015 %	0.015 %	
Silicon, Si	0.20 %	0.20 %	
Sulfur, S	0.0020 %	0.0020 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China