

Saint-Gobain CHR® 2283-2 Extruded PTFE Film Backing Acrylic Adhesive Pressure Sensitive Tape

Category : Polymer , Adhesive , Tape , Thermoplastic , Acrylic (PMMA)

Material Notes:

Description: PTFE films provide a conformable release surface and exhibit a remarkably low coefficient of friction and non-stick properties. PTFE films have high temperature resistance and are virtually unaffected by all chemicals. At elevated temperatures, PTFE film still retains excellent tensile strength. Service temperatures range from -100°F to +500°F (-73°C to 260°C). This tape uses an acrylic adhesive system. Acrylic adhesives perform in continuous operating temperatures from -40°F to +375°F (-40°C to +188°C). Benefits include exceptional solvent resistance, excellent adhesion to metal, superior weathering and aging characteristics. Acrylics have an excellent shelf life, and when exposed to elevated temperatures, their ability to wet-out improves thus increasing both adhesion and tack properties. All data based on a 0.004 inch test sample. (Thickness given is for both backing and adhesive. Backing thickness is .002 inches.) Information provided by Saint Gobain Performance Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Saint-Gobain-CHR-2283-2-Extruded-PTFE-Film-Backing-Acrylic-Adhesive-Pressure-Sensitive-Tape.php

Mechanical Properties	Metric	English	Comments
Elongation at Break	150 %	150 %	
Tear Strength	5.26 kN/m	30.0 pli	Initial Tear Strength

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	177 °C	350 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	98.4 kV/mm	2500 kV/in	
Dielectric Breakdown	10000 V	10000 V	

Descriptive Properties	Value	Comments
Color	Rust	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China