

Saint-Gobain CHR® 2285-2 Extruded PTFE Film Backing Silicone Adhesive Pressure Sensitive Tape

Category: Polymer, Adhesive, Tape, Thermoset, Silicone

Material Notes:

Description: PTFE films provide a conformable release surface and exhibit a remarkably low coefficient of friction and non-stick properties. PTFE films have high temperature resistance and are virtually unaffected by all chemicals. At elevated temperatures, PTFE film still retains excellent tensile strength. Service temperatures range from $-100\mathack{\hat{A}}$ °F to $+500\mathack{\hat{A}}$ °F ($-73\mathack{\hat{A}}$ °C to $260\mathack{\hat{A}}$ °C). This tape uses a silicone adhesive system. Perfect for extreme temperature applications, silicone adhesives perform in continuous operating temperatures from $-100\mathack{\hat{A}}$ °F to $500\mathack{\hat{A}}$ °C to $260\mathack{\hat{A}}$ °C. Silicone-based adhesive systems exhibit good chemical resistance, retain electrical properties, and remove cleanly with little or no residue. All data based on a 0.0035 inch test sample. (Thickness given is for both backing and adhesive. Backing thickness is .002 inches.) Information provided by Saint Gobain Performance Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Saint-Gobain-CHR-2285-2-Extruded-PTFE-Film-Backing-Silicone-Adhesive-Pressure-Sensitive-Tape.php

Mechanical Properties	Metric	English	Comments
Elongation at Break	175 %	175 %	
Tear Strength	5.26 kN/m	30.0 pli	Initial Tear Strength

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	260 °C	500 °F	
Minimum Service Temperature, Air	-73.3 °C	-100 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	101 kV/mm	2570 kV/in	
Dielectric Breakdown	9000 V	9000 V	

Descriptive Properties	Value	Comments
Color	Rust	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers



Address: United North Road 215, Fengxian District, Shanghai City, China