

## Saint-Gobain CHR® 2915-10 Glass Cloth Backing Silicone Adhesive Pressure Sensitive Tape

Category: Polymer, Adhesive, Tape, Thermoset, Silicone

## **Material Notes:**

Description: Glass cloth offers excellent abrasion resistance and mechanical properties, as well as high tensile strength and extreme temperature resistance. Service temperatures range from  $-100 \hat{A}^{\circ} F$  to  $+500 \hat{A}^{\circ} F$  ( $-73 \hat{A}^{\circ} C$  to  $+107 \hat{A}^{\circ} C$ ). Highly conformable and flexible, glass cloth has the unique ability to absorb insulating varnishes, which makes them an excellent choice in the electrical market. Applications include electrical insulation, coil and motor wrappings, and general industrial applications. This tape uses a silicone adhesive system. Perfect for extreme temperature applications, silicone adhesives perform in continuous operating temperatures from  $-100 \hat{A}^{\circ} F$  to  $500 \hat{A}^{\circ}$  ( $-73 \hat{A}^{\circ} C$  to  $260 \hat{A}^{\circ} C$ ). Silicone-based adhesive systems exhibit good chemical resistance, retain electrical properties, and remove cleanly with little or no residue. All data based on a 0.01 inch test sample. (Thickness given is for both backing and adhesive. Backing thickness is .0055 inches.) Information provided by Saint Gobain Performance Products.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Saint-Gobain-CHR-2915-10-Glass-Cloth-Backing-Silicone-Adhesive-Pressure-Sensitive-Tape.php

Mechanical Properties	Metric	English	Comments
Tear Strength	30.7 kN/m	175 pli	Initial Tear Strength

Thermal Properties	Metric	English	Comments	
Maximum Service Temperature, Air	260 °C	500 °F		
Minimum Service Temperature, Air	-73.3 °C	-100 °F		

Electrical Properties	Metric	English	Comments
Dielectric Strength	19.7 kV/mm	500 kV/in	
Dielectric Breakdown	5000 V	5000 V	

Descriptive Properties	Value	Comments
Color	White	

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China