

Saint-Gobain CHR® 2975-8R Glass-Silicone Backing Silicone Adhesive Pressure Sensitive Tape

Category: Polymer, Adhesive, Tape, Thermoset, Silicone

Material Notes:

Description: Silicone glass provides temperature resistance from $-85 {\hat {\rm A}}^{\circ} {\rm F}$ to $+500 {\hat {\rm A}}^{\circ} {\rm F}$ ($-62 {\hat {\rm A}}^{\circ} {\rm C}$ to $+260 {\hat {\rm A}}^{\circ} {\rm C}$) and exceptional tensile strength and abrasion resistance. Applications include thermal spray, grit blasting, electrical and thermal insulation gaskets, heat sealing, and diaphragms. This tape uses a silicone adhesive system. Perfect for extreme temperature applications, silicone adhesives perform in continuous operating temperatures from $-100 {\hat {\rm A}}^{\circ} {\rm F}$ to $500 {\hat {\rm A}}^{\circ}$ ($-73 {\hat {\rm A}}^{\circ} {\rm C}$ to $260 {\hat {\rm A}}^{\circ} {\rm C}$). Silicone-based adhesive systems exhibit good chemical resistance, retain electrical properties, and remove cleanly with little or no residue. All data based on a 0.0105 inch test sample. (Thickness given is for both backing and adhesive. Backing thickness is .007 inches.) Information provided by Saint Gobain Performance Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Saint-Gobain-CHR-2975-8R-Glass-Silicone-Backing-Silicone-Adhesive-Pressure-Sensitive-Tape.php

Mechanical Properties	Metric	English	Comments
Elongation at Break	5.0 %	5.0 %	
Tear Strength	26.3 kN/m	150 pli	Initial Tear Strength

Thermal Properties	Metric	English	Comments	
Maximum Service Temperature, Air	260 °C	500 °F		
Minimum Service Temperature, Air	-73.3 °C	-100 °F		

Electrical Properties	Metric	English	Comments
Dielectric Strength	26.3 kV/mm	667 kV/in	
Dielectric Breakdown	7000 V	7000 V	

Descriptive Properties	Value	Comments
Color	Blue	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China