

Saint-Gobain CHR® SG35-05(R) Industrial Glass-PTFE Backing Silicone Adhesive Pressure Sensitive Tape

Category : Polymer , Adhesive , Tape , Thermoset , Silicone

Material Notes:

Description: PTFE glass provide dimensional stability, high tensile strength and edge tear, operates over a temperature range from -100°F to +500°F (-73°C to 260°C), and offers better abrasion resistance than uncoated glass cloth. The PTFE surface offers quick release and chemical resistance characteristics. Anti-static PTFE glass yields improved thermal conductivity and static dissipation. Available with silicone or acrylic adhesives, PTFE glass applications include heat sealing and low friction release surface liners for conveyors. This tape uses a silicone adhesive system. Perfect for extreme temperature applications, silicone adhesives perform in continuous operating temperatures from -100°F to 500°F (-73°C to 260°C). Silicone-based adhesive systems exhibit good chemical resistance, retain electrical properties, and remove cleanly with little or no residue. Specification Notes: 21CFR177.1550 compliant. All data based on a 0.0073 inch test sample. (Thickness given is for both backing and adhesive. Backing thickness is .005 inches.) Information provided by Saint Gobain Performance Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Saint-Gobain-CHR-SG35-05R-Industrial-Glass-PTFE-Backing-Silicone-Adhesive-Pressure-Sensitive-Tape.php

| Mechanical Properties | Metric | English | Comments |
|-----------------------|-----------|----------|-----------------------|
| Elongation at Break | <= 5.0 % | <= 5.0 % | |
| Tear Strength | 28.0 kN/m | 160 pli | Initial Tear Strength |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|----------|---------|----------|
| Maximum Service Temperature, Air | 260 °C | 500 °F | |
| Minimum Service Temperature, Air | -73.3 °C | -100 °F | |

| Descriptive Properties | Value | Comments |
|------------------------|---------|----------|
| Color | Natural | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China