

## Saint-Gobain CHR<sup>®</sup> TV350 Skived PTFE Film Backing Silicone Adhesive Pressure Sensitive Tape

Category : Polymer , Adhesive , Tape , Thermoset , Silicone

### Material Notes:

Description: PTFE films provide a conformable release surface and exhibit a remarkably low coefficient of friction and non-stick properties. PTFE films have high temperature resistance and are virtually unaffected by all chemicals. At elevated temperatures, PTFE film still retains excellent tensile strength. Service temperatures range from -100<sup>°</sup>F to +500<sup>°</sup>F (-73<sup>°</sup>C to 260<sup>°</sup>C). This tape uses a silicone adhesive system. Perfect for extreme temperature applications, silicone adhesives perform in continuous operating temperatures from -100<sup>°</sup>F to 500<sup>°</sup>F (-73<sup>°</sup>C to 260<sup>°</sup>C). Silicone-based adhesive systems exhibit good chemical resistance, retain electrical properties, and remove cleanly with little or no residue. Specification Notes: MIL-I-123594C Type 1, Class 1, A-A-59474. All data based on a 0.0035 inch test sample. (Thickness given is for both backing and adhesive. Backing thickness is .002 inches.) Information provided by Saint Gobain Performance Products.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Saint-Gobain-CHR-TV350-Skived-PTFE-Film-Backing-Silicone-Adhesive-Pressure-Sensitive-Tape.php](http://www.lookpolymers.com/polymer_Saint-Gobain-CHR-TV350-Skived-PTFE-Film-Backing-Silicone-Adhesive-Pressure-Sensitive-Tape.php)

Mechanical Properties	Metric	English	Comments
Elongation at Break	250 %	250 %	
Tear Strength	2.63 kN/m	15.0 pli	Initial Tear Strength

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	260 <sup>°</sup> C	500 <sup>°</sup> F	
Minimum Service Temperature, Air	-73.3 <sup>°</sup> C	-100 <sup>°</sup> F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	87.8 kV/mm	2230 kV/in	
Dielectric Breakdown	7800 V	7800 V	

Descriptive Properties	Value	Comments
Color	White	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China