

Saint-Gobain Spectrosil® 1000 Optical Fused Quartz

Category : Ceramic , Glass , Oxide , Silicon Oxide

Material Notes:

Spectrosil® 1000 grade is used for non-transmissive mirrors and substrates, and other high purity components which do not require specified optical transmission. Spectrosil® is a synthetic fused silica manufactured using a patented, environmentally friendly process that results in a virtually chlorine-free material of exceptional purity which is bubble-free and fluorescence-free. Available in ingot, rod, tube, and components. General properties of Fused Silica and Fused quartz: A very wide transmission range from UV to near IR; extremely high optical transmission, excellent resistance to high power laser energy, excellent homogeneity, high temperature resistance, very low thermal expansion (resistance to thermal shock), and chemical inertness. General uses for optical quartz are microlithography optical systems, optical fibers, photomasks, laser optics, LCD displays, light guides, optical, IR , and UV windows, spectrophotometer cells, slides, optical pyrometers, and lamp bodies/components. Information provided by Saint-Gobain Quartz PLC.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Saint-Gobain-Spectrosil-1000-Optical-Fused-Quartz.php

Physical Properties	Metric	English	Comments
Density	2.21 g/cc	0.0798 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Knoop	820	820	
Vickers Microhardness	1050 - 1350	1050 - 1350	kg/m ² Vickers DPH
Hardness, Mohs	7.0	7.0	
Modulus of Elasticity	74.0 GPa	10700 ksi	
Flexural Strength	50.0 MPa	7250 psi	Bending Strength
Compressive Strength	1100 MPa	160000 psi	
Poissons Ratio	0.17	0.17	
Shear Modulus	31.0 GPa	4500 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	0.540 Åµm/m-Å°C @Temperature 0.000 - 1000 Å°C	0.300 Åµin/in-Å°F @Temperature 32.0 - 1830 Å°F	average
Specific Heat Capacity	0.750 J/g-Å°C	0.179 BTU/lb-Å°F	
Thermal Conductivity	2.00 W/m-K	13.9 BTU-in/hr-ftÅ²-Å°F	

Maximum Service Temperature, Air Thermal Properties	1050 Â°C Metric	1920 Â°F English	Normal Conditions Comments
	1350 Â°C	2460 Â°F	Extended periods if cycles remain above 300Â°C
	1350 Â°C	2460 Â°F	
	1650 Â°C	3000 Â°F	Quick Immersion
Softening Point	1710 Â°C	3110 Â°F	Varies with thermal history
Annealing Point	1100 Â°C	2010 Â°F	Varies with thermal history
Strain Point	990 Â°C	1810 Â°F	Varies with thermal history

Optical Properties	Metric	English	Comments
Refractive Index	1.457	1.457	n_{He-Ne}; Temperature Coefficient = 10.0 ppm/K
	@Wavelength 632.8 nm	@Wavelength 632.8 nm	
	1.4667	1.4667	n_g; Temperature Coefficient = 10.6 ppm/K
	@Wavelength 435.83 nm	@Wavelength 435.83 nm	

Component Elements Properties	Metric	English	Comments
SiO2	>= 99.999 %	>= 99.999 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	2.00e+10 ohm-cm	2.00e+10 ohm-cm	@Temperature 1470 Â°F
	@Temperature 800 Â°C		
Dielectric Constant	3.78	3.78	@Frequency 100 - 2.50e+10 Hz
	@Frequency 100 - 2.50e+10 Hz		
Dissipation Factor	0.000060	0.000060	@Frequency 1e+9 Hz
	@Frequency 1e+9 Hz		
	0.00075	0.00075	@Frequency 1000 Hz
	@Frequency 1000 Hz		

Descriptive Properties	Value	Comments
Bubble Class	0	per DIN 58927
Bubbles; Sum of CSA	< 0.03 mmÂ²/100 cmÂ³	

Inclusions Descriptive Properties	Value	Comments
--------------------------------------	-------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China