

Samsung Cheil Industries Starex® HG-0760AT ABS, Unreinforced

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Information provided by Samsung Cheil Industries.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samsung-Cheil-Industries-Starex-HG-0760AT-ABS-Unreinforced.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.07 g/cc	1.07 g/cc	ASTM D792
Melt Flow	3.7 g/10 min @Load 5.00 kg, Temperature 200 Â°C	3.7 g/10 min @Load 11.0 lb, Temperature 392 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	110	110	ASTM D785
Tensile Strength, Yield	39.2 MPa	5690 psi	5 mm/min; ASTM D638
Flexural Strength	60.8 MPa	8820 psi	2.8 mm/min; ASTM D790
Flexural Modulus	2.16 GPa	313 ksi	2.8 mm/min; ASTM D790
Izod Impact, Notched	2.06 J/cm @Thickness 6.35 mm	3.86 ft-lb/in @Thickness 0.250 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	82.0 Â°C @Thickness 6.40 mm	180 Â°F @Thickness 0.252 in	ASTM D648
Vicat Softening Point	95.0 Â°C	203 Â°F	B/50; ISO R306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China