

Samsung Cheil Industries Starex® SR-0310FM ABS, Unreinforced Heat Resistant

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Heat Resistant, Molded

Material Notes:

Information provided by Samsung Cheil Industries.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samsung-Cheil-Industries-Starex-SR-0310FM-ABS-Unreinforced-Heat-Resistant.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Water Absorption	0.30 % @Temperature 23.0 Â°C	0.30 % @Temperature 73.4 Â°F	ASTM D570
Linear Mold Shrinkage, Flow	0.0050 - 0.0060 cm/cm @Thickness 3.20 mm	0.0050 - 0.0060 in/in @Thickness 0.126 in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0060 cm/cm @Thickness 3.20 mm	0.0060 in/in @Thickness 0.126 in	ASTM D955
Melt Flow	18 g/10 min @Load 10.0 kg, Temperature 220 Â°C	18 g/10 min @Load 22.0 lb, Temperature 428 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	109	109	ASTM D785
Tensile Strength, Yield	39.2 MPa	5690 psi	5 mm/min; ASTM D638
Elongation at Break	35 %	35 %	5 mm/min; ASTM D638
Flexural Strength	62.8 MPa	9110 psi	2.8 mm/min; ASTM D790
Flexural Modulus	2.06 GPa	299 ksi	2.8 mm/min; ASTM D790
Izod Impact, Notched	1.77 J/cm @Thickness 6.35 mm	3.31 ft-lb/in @Thickness 0.250 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	90.0 Â°C @Thickness 6.40 mm	194 Â°F @Thickness 0.252 in	ASTM D648
Vicat Softening Point	104 Â°C	219 Â°F	B/50; ISO R306

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China