

## Samyang Tramid® 910 PA66/PA6

Category : Polymer , Thermoplastic , Nylon

### Material Notes:

Strong with excellent thermal resistance. Abrasion resistance, chemical resistance and oil resistance are excellent. Applications: Automotive knob types, door handles and mirror housings Connectors Cable ties Harness clips Tubes Fasteners Castor wheels Hose clips Vacuum hose Hood stay Information provided by Samyang.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Samyang-Tramid-910-PA66PA6.php](http://www.lookpolymers.com/polymer_Samyang-Tramid-910-PA66PA6.php)

| Physical Properties   | Metric              | English             | Comments  |
|-----------------------|---------------------|---------------------|-----------|
| Specific Gravity      | 1.11 g/cc           | 1.11 g/cc           | ASTM D792 |
| Water Absorption      | 1.4 %               | 1.4 %               | ASTM D570 |
| Linear Mold Shrinkage | 0.015 - 0.017 cm/cm | 0.015 - 0.017 in/in | ASTM D955 |

| Mechanical Properties   | Metric                           | English                               | Comments  |
|-------------------------|----------------------------------|---------------------------------------|-----------|
| Tensile Strength        | 64.7 MPa                         | 9390 psi                              | ASTM D638 |
| Elongation at Break     | 4.0 %                            | 4.0 %                                 | ASTM D638 |
| Flexural Yield Strength | 147 MPa                          | 21300 psi                             | ASTM D790 |
| Flexural Modulus        | 8.14 GPa                         | 1180 ksi                              | ASTM D790 |
| Izod Impact, Notched    | 0.490 J/cm<br>@Thickness 3.17 mm | 0.918 ft-lb/in<br>@Thickness 0.125 in | ASTM D256 |

| Thermal Properties                          | Metric   | English | Comments   |
|---------------------------------------------|----------|---------|------------|
| Melting Point                               | 261 Â°C  | 502 Â°F | ASTM D3418 |
| Deflection Temperature at 0.46 MPa (66 psi) | 192 Â°C  | 378 Â°F | ASTM D648  |
| Deflection Temperature at 1.8 MPa (264 psi) | 56.0 Â°C | 133 Â°F | ASTM D648  |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China