

Samyang Tribit® 1500G15K PBT, Reinforced Impact

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 20% Glass Fiber Filled

Material Notes:

Crystallization is fast, formability is excellent and thermal resistance, chemical resistance, electrical properties and abrasion resistance are excellent. 1500G15K is a reinforced, impact grade. Applications: Connectors (insulation characteristics) Information provided by Samyang.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samyang-Tribit-1500G15K-PBT-Reinforced-Impact.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.50 g/cc	1.50 g/cc	ASTM D792
Water Absorption	0.080 %	0.080 %	ASTM D570
Linear Mold Shrinkage	0.0020 - 0.012 cm/cm	0.0020 - 0.012 in/in	ASTM D955
Melt Flow	50 g/10 min @Load 2.16 kg, Temperature 250 Â°C	50 g/10 min @Load 4.76 lb, Temperature 482 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	119	119	ASTM D785
Tensile Strength	83.4 MPa	12100 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Yield Strength	118 MPa	17100 psi	ASTM D790
Flexural Modulus	3.24 GPa	469 ksi	ASTM D790
Izod Impact, Notched	0.490 J/cm @Thickness 3.17 mm	0.918 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	30.0 Âµm/m-Â°C	16.7 Âµin/in-Â°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	225 Â°C	437 Â°F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	210 Â°C	410 Â°F	ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257

Dielectric Constant Electrical Properties	3.2 Metric	3.2 English	ASTM D150 Comments
Dielectric Strength	21.0 kV/mm	533 kV/in	ASTM D149
Dissipation Factor	0.020	0.020	ASTM D150
Arc Resistance	150 sec	150 sec	ASTM D495

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China