

Samyang Triel® 5401BM Thermoplastics Polyetherester Elastomer, Blow Molding

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyester, TP , Polyether Ester Elastomer

Material Notes:

Excellent mechanical characteristics, elasticity, thermal resistance and chemical resistance. 5401BM is for blow molding applications. Applications: Automotive - CVJB and Bellows. Information provided by Samyang.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samyang-Triel-5401BM-Thermoplastics-Polyetherester-Elastomer-Blow-Molding.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.15 g/cc	1.15 g/cc	ASTM D792
Water Absorption	0.50 %	0.50 %	ASTM D570
Linear Mold Shrinkage	0.015 - 0.017 cm/cm	0.015 - 0.017 in/in	ASTM D955
Melt Flow	1.0 g/10 min @Load 2.16 kg, Temperature 230 Â°C	1.0 g/10 min @Load 4.76 lb, Temperature 446 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	40	40	ASTM D2240
Tensile Strength, Ultimate	22.6 MPa	3270 psi	ASTM D638
Tensile Strength, Yield	3.92 MPa @Strain 5.00 %	569 psi @Strain 5.00 %	ASTM D638
	5.88 MPa @Strain 10.0 %	853 psi @Strain 10.0 %	ASTM D638
	10.8 MPa @Strain 50.0 %	1560 psi @Strain 50.0 %	ASTM D638
Flexural Yield Strength	3.92 MPa	569 psi	ASTM D790
Flexural Modulus	0.0637 GPa	9.25 ksi	ASTM D790
Izod Impact, Notched	NB @Thickness 3.17 mm, Temperature -40.0 Â°C	NB @Thickness 0.125 in, Temperature -40.0 Â°F	ASTM D256
	NB @Thickness 3.17 mm, Temperature 23.0 Â°C	NB @Thickness 0.125 in, Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	200 Â°C	392 Â°F	ASTM D2117
Deflection Temperature at 0.46 MPa (66 psi)	56.0 Â°C	133 Â°F	ASTM D648
Vicat Softening Point	155 Â°C	311 Â°F	ASTM D1525

Descriptive Properties	Value	Comments
Flexible Rate	> 400%	ASTM D638

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China