

Samyang Trirex® 3015NF Polycarbonate, Flame Retardancy

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Unreinforced, Flame Retardant

Material Notes:

PC is characterized by its excellent impact resistance, dimensional stability and excellent thermal resistance. 3015NF is a flame retardant grade. Applications: Mobile Phone - battery case. Information provided by Samyang.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samyang-Trirex-3015NF-Polycarbonate-Flame-Retardancy.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Water Absorption	0.15 %	0.15 %	ASTM D570
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Flow	50 g/10 min @Load 1.20 kg, Temperature 300 Â°C	50 g/10 min @Load 2.65 lb, Temperature 572 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	ASTM D785
Tensile Strength	54.9 MPa	7970 psi	ASTM D638
Elongation at Break	100 %	100 %	ASTM D638
Flexural Yield Strength	80.4 MPa	11700 psi	ASTM D790
Flexural Modulus	2.26 GPa	327 ksi	ASTM D790
Izod Impact, Notched	0.981 J/cm @Thickness 3.17 mm	1.84 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	55.0 Âµm/m-Â°C	30.6 Âµin/in-Â°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	87.0 Â°C	189 Â°F	ASTM D648
Flammability, UL94	V-0 @Thickness 0.500 mm	V-0 @Thickness 0.0197 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	4.00e+16 ohm-cm	4.00e+16 ohm-cm	ASTM D257

Electrical Properties	Metric	English	Comments
Dielectric Strength	30.0 kV/mm	762 kV/in	ASTM D149
Dissipation Factor	0.0090	0.0090	ASTM D150
Arc Resistance	90 sec	90 sec	ASTM D495

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China