

Sapco 98% Aluminum Oxide

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Information provided by Sapco.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sapco-98-Aluminum-Oxide.php

Physical Properties	Metric	English	Comments
Density	3.90 g/cc	0.141 lb/in ³	
Open Porosity	0.00 %	0.00 %	
Weibull Modulus	>= 10	>= 10	

Mechanical Properties	Metric	English	Comments
Hardness, Mohs	9.0	9.0	
Tensile Strength, Ultimate	250 MPa	36300 psi	
Modulus of Elasticity	350 GPa	50800 ksi	
Flexural Strength	350 MPa	50800 psi	
Compressive Strength	2600 MPa	377000 psi	
Poissons Ratio	0.22	0.22	
Shear Modulus	143 GPa	20700 ksi	Calculated

Thermal Properties	Metric	English	Comments
CTE, linear	8.20 Åµm/m-Å°C @Temperature 20.0 Å°C	4.56 Åµin/in-Å°F @Temperature 68.0 Å°F	
Specific Heat Capacity	0.880 J/g-Å°C	0.210 BTU/lb-Å°F	
Thermal Conductivity	25.0 W/m-K	174 BTU-in/hr-ftÅ²-Å°F	
Maximum Service Temperature, Air	1700 Å°C	3090 Å°F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	
Dielectric Constant	9.2	9.2	

Electrical Properties	@Frequency 1e+6 Hz Metric	@Frequency 1e+6 Hz English	Comments
Dielectric Strength	20.0 kV/mm	508 kV/in	AC
Dissipation Factor	0.00020 @Frequency 1e+6 Hz	0.00020 @Frequency 1e+6 Hz	
Dielectric Loss Index	0.0018	0.0018	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China