

Sax Polymers SAXALEN PPC343G20 Polypropylene Copolymer, 20% Glass Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Glass Fiber Filler

Material Notes:

SAXALEN PPC343G20 is a 20% glass filled Polypropylene - Copolymer intended for injection molding. Information provided by SAX Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sax-Polymers-SAXALEN-PPC343G20-Polypropylene-Copolymer-20-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.02 g/cc	0.0368 lb/in ³	
Melt Flow	20 g/10 min @Load 2.16 kg, Temperature 230 °C	20 g/10 min @Load 4.76 lb, Temperature 446 °F	from MVR; ISO 1033

Mechanical Properties	Metric	English	Comments
Tensile Strength	47.0 MPa	6820 psi	5 mm/min; ISO 527-1
Elongation at Break	4.0 %	4.0 %	5 mm/min; ISO 527-1
Tensile Modulus	3.90 GPa	566 ksi	1 mm/min; ISO 527-1
Flexural Strength	76.0 MPa	11000 psi	2 mm/min; ISO 178
Flexural Modulus	3.20 GPa	464 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	8.00 kJ/m ² @Temperature -30.0 °C	3.81 ft-lb/in ² @Temperature -22.0 °F	ISO 180/1A
	11.0 kJ/m ² @Temperature 23.0 °C	5.23 ft-lb/in ² @Temperature 73.4 °F	ISO 180/1A
Izod Impact, Unnotched (ISO)	32.0 kJ/m ² @Temperature -30.0 °C	15.2 ft-lb/in ² @Temperature -22.0 °F	ISO 180/1U
	34.0 kJ/m ² @Temperature 23.0 °C	16.2 ft-lb/in ² @Temperature 73.4 °F	ISO 180/1U
Charpy Impact Unnotched	3.50 J/cm ² @Temperature -30.0 °C	16.7 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eU
	4.00 J/cm ² @Temperature 23.0 °C	19.0 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eU

Mechanical Properties	Metric J/cm^2	English lb/in^2	Comments
Charpy Impact, Notched	@Temperature -30.0 °C	@Temperature -22.0 °F	ISO 179/1eA
	1.00 J/cm ²	4.76 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	117 °C	243 °F	80*10*4 s=60mm; ISO 75-1 a
Vicat Softening Point	103 °C	217 °F	B/120; ISO 306

Processing Properties	Metric	English	Comments
Melt Temperature	220 - 250 °C	428 - 482 °F	
Mold Temperature	40.0 - 70.0 °C	104 - 158 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China