

Sax Polymers SAXALEN PPH329B20 Polypropylene Homopolymer, 20% Glass Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Glass Fiber Filler

Material Notes:

SAXALEN PPH329B20 is a 20% glass beads filled Polypropylene - Homopolymer intended for injection molding. Low shrinkage, low warpage grade information provided by SAX Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sax-Polymers-SAXALEN-PPH329B20-Polypropylene-Homopolymer-20-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.03 g/cc	0.0372 lb/in ³	
Melt Flow	10 g/10 min @Load 2.16 kg, Temperature 230 °C	10 g/10 min @Load 4.76 lb, Temperature 446 °F	from MVR; ISO 1033

Mechanical Properties	Metric	English	Comments
Tensile Strength	25.0 MPa	3630 psi	5 mm/min; ISO 527-1
Elongation at Break	100 %	100 %	5 mm/min; ISO 527-1
Tensile Modulus	1.60 GPa	232 ksi	1 mm/min; ISO 527-1
Flexural Strength	40.0 MPa	5800 psi	2 mm/min; ISO 178
Flexural Modulus	1.60 GPa	232 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	2.00 kJ/m ² @Temperature -30.0 °C	0.952 ft-lb/in ² @Temperature -22.0 °F	ISO 180/1A
	4.00 kJ/m ² @Temperature 23.0 °C	1.90 ft-lb/in ² @Temperature 73.4 °F	ISO 180/1A
Izod Impact, Unnotched (ISO)	13.0 kJ/m ² @Temperature -30.0 °C	6.19 ft-lb/in ² @Temperature -22.0 °F	ISO 180/1U
	27.0 kJ/m ² @Temperature 23.0 °C	12.8 ft-lb/in ² @Temperature 73.4 °F	ISO 180/1U
Charpy Impact Unnotched	2.00 J/cm ² @Temperature -30.0 °C	9.52 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eU
	3.50 J/cm ² @Temperature 23.0 °C	16.7 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eU

Mechanical Properties	Metric /cm ²	English -lb/in ²	Comments
Charpy Impact, Notched	@Temperature -30.0 °C	@Temperature -22.0 °F	ISO 179/1eA
	0.200 J/cm ²	0.952 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	65.0 °C	149 °F	80*10*4 s=60mm; ISO 75-1 a
Vicat Softening Point	100 °C	212 °F	B/120; ISO 306

Processing Properties	Metric	English	Comments
Melt Temperature	220 - 250 °C	428 - 482 °F	
Mold Temperature	40.0 - 70.0 °C	104 - 158 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China